

NT-MIL

Flexible, rugged, modified elastomeric heat-shrinkable tubing

NT-MIL modified elastomeric heatshrinkable tubing offers outstanding resistance to abrasion and physical abuse while providing flexibility and strain relief needed in many harnessing applications. NT-MIL tubing is widely used for insulation, strain relief and abrasion protection on cable harnesses and wire bundles in the military and aerospace industries. It meets the stringent requirements of AMS-DTL-23053/1, Classes 1 and 2.

Temperature rating

NT-MIL tubing remains flexible at temperatures as low as -70°C without cracking. It also withstands heat shock at 200°C without dripping, flowing or cracking.

NT-MIL tubing is resistant to common fluids and solvents including aviation and ground vehicle fuels, lubricating oil, and hydraulic fluids. It retains excellent physical and electrical properties following exposure. No special skills are required to install NT-MIL tubing. Using standard heating tools, one operator can complete an installation in minutes, substantially reducing labor costs.

NT-MIL tubing is supplied in a wide range of sizes. Because NT-MIL is heat-shrinkable, each size can accommodate a variety of harness sizes, minimizing inventory and related costs.

Full recovery temperature:	135°C
Continuous operating temperature:	-70°C to 121°C

Specifications*

Туре	Raychem	Military	
NT-MIL	RW-3030	AMS-DTL-23053/1, Cl. 1 and 2	
*When ordering alv	ways specify latest issue		

*When ordering, always specify latest issue.

Dimensions (millimeters/inches)



in.) Inded Ipplied 0.125 0.187	d (ma Recov after H 1.6 2.4			g** 0.026 ± 0.008	Size	D (mir Expar as su 25.4	nded oplied		vered neating	W Recovered after heatin	g**
1pplied 0.125	after I 1.6	neating 0.062	after heating 0.66 ± 0.20	5	Size	as su	oplied	after I	neating	after heatin	g**
0.125	1.6	0.062	0.66 ± 0.20	5	Size		•		5		g**
				0.026 ± 0.008	1	25.4	1 000	445			
0.187	2.4	0.093	0.04 . 0.05			2011	1.000	14.5	0.570	1.77 ± 0.51	0.070 ± 0.020
		0.070	0.84 ± 0.25	0.033 ± 0.010	1 1/4	31.8	1.250	18.1	0.714	2.20 ± 0.51	0.087 ± 0.020
0.250	3.6	0.143	0.89 ± 0.25	0.035 ± 0.010	1 1/2	38.1	1.500	21.8	0.857	2.41 ± 0.51	0.095 ± 0.020
0.375	5.4	0.211	1.01 ± 0.25	0.040 ± 0.010	1 3/4	44.5	1.750	25.4	1.000	2.71 ± 0.51	0.107 ± 0.020
0.500	7.3	0.286	1.21 ± 0.38	0.048 ± 0.015	2	50.8	2.000	29.0	1.140	2.79 ± 0.51	0.110 ± 0.020
0.625	9.1	0.357	1.32 ± 0.38	0.052 ± 0.015	3	76.2	3.000	43.4	1.710	3.17 ± 0.51	0.125 ± 0.020
0.750	10.9	0.428	1.44 ± 0.38	0.057 ± 0.015	4	101.6	4.000	57.9	2.280	3.55 ± 0.51	0.140 ± 0.020
0.875	12.7	0.500	1.65 ± 0.38	0.065 ± 0.015							
	0.625 0.750	0.6259.10.75010.90.87512.7	0.6259.10.3570.75010.90.4280.87512.70.500	0.625 9.1 0.357 1.32 ± 0.38 0.750 10.9 0.428 1.44 ± 0.38 0.875 12.7 0.500 1.65 ± 0.38	0.625 9.1 0.357 1.32 ± 0.38 0.052 ± 0.015 0.750 10.9 0.428 1.44 ± 0.38 0.057 ± 0.015 0.875 12.7 0.500 1.65 ± 0.38 0.065 ± 0.015	0.625 9.1 0.357 1.32 ± 0.38 0.052 ± 0.015 3 0.750 10.9 0.428 1.44 ± 0.38 0.057 ± 0.015 4 0.875 12.7 0.500 1.65 ± 0.38 0.065 ± 0.015 4	0.625 9.1 0.357 1.32 ± 0.38 0.052 ± 0.015 3 76.2 0.750 10.9 0.428 1.44 ± 0.38 0.057 ± 0.015 4 101.6	0.625 9.1 0.357 1.32 ± 0.38 0.052 ± 0.015 3 76.2 3.000 0.750 10.9 0.428 1.44 ± 0.38 0.057 ± 0.015 4 101.6 4.000 0.875 12.7 0.500 1.65 ± 0.38 0.065 ± 0.015 4 101.6 4.000	0.625 9.1 0.357 1.32 ± 0.38 0.052 ± 0.015 3 76.2 3.000 43.4 0.750 10.9 0.428 1.44 ± 0.38 0.057 ± 0.015 4 101.6 4.000 57.9 0.875 12.7 0.500 1.65 ± 0.38 0.065 ± 0.015 4 101.6 4.000 57.9	0.625 9.1 0.357 1.32 ± 0.38 0.052 ± 0.015 3 76.2 3.000 43.4 1.710 0.750 10.9 0.428 1.44 ± 0.38 0.057 ± 0.015 4 101.6 4.000 57.9 2.280 0.875 12.7 0.500 1.65 ± 0.38 0.065 ± 0.015 4 101.6 4.000 57.9 2.280	0.625 9.1 0.357 1.32 ± 0.38 0.052 ± 0.015 3 76.2 3.000 43.4 1.710 3.17 ± 0.51 0.750 10.9 0.428 1.44 ± 0.38 0.057 ± 0.015 4 101.6 4.000 57.9 2.280 3.55 ± 0.51

**Wall thickness will be less if tubing recovery is restricted during shrinkage.

Ordering information

Colors	Black
Size selection	Always order the largest size that will shrink snugly over the component being covered.
Standard packaging	On spools
Ordering description	Specify product name, size, and color; for example, NT-MIL 1/4-0 (0=Black).

Specification values

	Property	Unit		Requirement		Method of test
Material	Dimensions	mm <i>(inche</i>	es)	See Reverse		ASTM D 2671
	Longitudinal change	percent		+1, -10		ASTM D 2671
	Tensile strength	psi <i>(Mpa</i>)		1500 <i>(10.3)</i> minimum		ASTM D 412
	Ultimate elongation	percent		225 minimum		ASTM D 412
	Tensile stress at 200% elongation	psi <i>(Mpa</i>)		1500 <i>(10.3)</i> maximum	ı	AMS-DTL-23053
	Restricted shrinkage (30 minutes at 135°C/275°F)			No cracks		AMS-DTL-23053
	Followed by test for:					
	Voltage withstand			Pass		
	Low temperature flexibility (4 hours at -70°C/-94°F)			No cracks		AMS-DTL-23053
	Heat shock (4 hours at 200°C/ <i>392°F</i>)			No cracks, flowing or dripping		AMS-DTL-23053
	Heat resistance (168 hours at 121°C/250°F)					ASTM D 2671
	Followed by tests for:					
	Tensile strength	psi <i>(Mpa)</i>		1200 <i>(8.3)</i> minimum		ASTM D 412
	Ultimate elongation	percent		175 minimum		ASTM D 412
	Dielectric strength	volts/mil <i>(k</i>	(v/mm)	Sizes up to 7/8: 300 (11.8) minimum Sizes 1 and larger:		ASTM D 2671
Electrical	Dielectric strength	volts/mil <i>(kv/mm)</i>		200 (7.8) minimum Sizes up to 7/8: 300 (11.8) minimum	ASTM D 2671	
				Sizes 1 and larger: 200 (7.8) minimum	5 1 and larger: (7.8) minimum	
	Volume resistivity	ohm-cm		1 x 10 ¹¹ minimum		ASTM D 876
Chemical	Copper mirror corrosion (16 hours at 150°C/302°F)			No pitting or corrosion		AMS-DTL-23053
	Copper contact corrosion (16 hours at 150°C/302°F)			No pitting or blacken of copper	ing	AMS-DTL-23053
	Flammability			Self-extinguishing in 15 seconds; 3 inches maximum burn lengtl		ASTM D 2671 Procedure A
	Fungus resistance			No growth		ASTM G 21
	Water absorption (24 hours at 23°C/73°F)	percent		1.0 maximum	ASTM D 570	
	Fluid resistance (24 hours at 23°C/73°F) in: JP-8 fuel (MIL-T-83133) Hydraulic fluid (MIL-H-5606) Lubricating oil (MIL-L-7808) Lubricating oil (MIL-L 23699) Salt water (5% salt) Anti-icing fluid (MIL-A-8243)					AMS-DTL-23053
	Followed by tests for:					
	Tensile strength	psi <i>(Mpa</i>)		1000 <i>(6.9)</i> minimum		ASTM D 412
	Ultimate elongation	percent		175 minimum		ASTM D 412
	Dielectric strength	volts/mil <i>(k</i>	(V/mm)	250 <i>(9.8)</i> minimum		ASTM D 2671
Note: Consult RW-3030 for spe Raychem is a trademark of Ty	ecific details about test procedures. co Electronics Corporation.					
Tyco Electronics Corporation 300 Constitution Drive Menlo Park, CA 94025-1164 JSA Tel: (800) 926-2425 (US & Can Tel: +1 (650) 361-3860 (All other	n Faraday Road Dorcan, Swindon, SI United Kingdom ada) Tel: +44 1793 52817			prito, Tama-ku Kanagawa 214-8533 900 5102	Asia Pacific Hea 26 Ang Mo Kio, Singapore 5695 Tel: +65 4866 1	, Industrial Park 2 507

All information, including illustrations, is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. Tyco Electronics Corporation makes no warranties as to the accuracy or completeness of the information, and disclaims any liability regarding its use. Tyco Electronics Corporation's only obligations are those in the Standard Terms and Conditions of Sale for these products and in no case will Tyco Electronics Corporation be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use, or misuse of the product. Tyco Electronics Corporation's Specifications are subject to change without notice. In addition, Tyco Electronics Corporation reserves the right to make changes in materials or processing without notification to the Buyer which do not affect compliance with any applicable specification.

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

TE Connectivity: NT-MIL-1-1/2-0-SP