

RT-375

Raychem

Very clear, thin-wall, flexible, fluoropolymer heat-shrinkable tubing

RT-375 is a highly flame-resistant, heat-shrinkable, thin-wall tubing that has excellent clarity. It is manufactured from a modified fluoropolymer whose properties include toughness, chemical resistance, and high-temperature performance.

A very thin wall gives RT-375 excellent flexibility.

Applications include protection of wire and cable markers subject to abuse; bundling and jacketing of wires and cables to protect them from mechanical and chemical abuse while permitting full inspectability of the item covered; and protection of electronic components without losing the ability to identify the part.

RT-375 is UL-recognized and CSA-certified at 150°C, 600 V, with a VW-1 flame-retardancy rating.

Temperature rating

Full recovery temperature:	150°C
Continuous operating temperature:	-55°C to 150°C
Recommended maximum temperature for use as a primary insulator:	135°C

Specifications*			117 .	®
Туре	Raychem	Military	UL	CSA
RT-375	RT-375	AMS-DTL-23053/18, Class 2	E85381 VW-1	LR31929 VW-1

^{*}When ordering, always specify latest issue.

Dimensions (millimeters/inches)



Inside	diameter			Wall thicknes	SS
D (mir	1.)	d (ma	x.)	W	
Expar	nded	Reco	vered	Recovered	
as su	pplied	after	heating	after heating	**
1.2	0.046	0.6	0.023	0.25 ± 0.05	0.010 ± 0.002
1.6	0.063	0.8	0.031	0.25 ± 0.05	0.010 ± 0.002
2.4	0.093	1.2	0.046	0.25 ± 0.05	0.010 ± 0.002
3.2	0.125	1.6	0.062	0.25 ± 0.05	0.010 ± 0.002
4.8	0.187	2.4	0.093	0.25 ± 0.05	0.010 ± 0.002
6.4	0.250	3.2	0.125	0.30 ± 0.08	0.012 ± 0.003
9.5	0.375	4.8	0.187	0.30 ± 0.08	0.012 ± 0.003
12.7	0.500	6.4	0.250	0.30 ± 0.08	0.012 ± 0.003
19.1	0.750	9.5	0.375	0.43 ± 0.08	0.017 ± 0.003
25.4	1.000	12.7	0.500	0.48 ± 0.08	0.019 ± 0.003
	D (min Expar as sup 1.2 1.6 2.4 3.2 4.8 6.4 9.5 12.7	1.6	D (min.) d (maximum) Expanded Record as supplied after 1.2 0.046 0.6 1.6 0.063 0.8 2.4 0.093 1.2 3.2 0.125 1.6 4.8 0.187 2.4 6.4 0.250 3.2 9.5 0.375 4.8 12.7 0.500 6.4 19.1 0.750 9.5	D (min.) d (max.) Expanded as supplied Recovered after heating 1.2 0.046 0.6 0.023 1.6 0.063 0.8 0.031 2.4 0.093 1.2 0.046 3.2 0.125 1.6 0.062 4.8 0.187 2.4 0.093 6.4 0.250 3.2 0.125 9.5 0.375 4.8 0.187 12.7 0.500 6.4 0.250 19.1 0.750 9.5 0.375	D (min.) d (max.) W Expanded as supplied Recovered Recovered after heating 1.2 0.046 0.6 0.023 0.25 \pm 0.05 1.6 0.063 0.8 0.031 0.25 \pm 0.05 2.4 0.093 1.2 0.046 0.25 \pm 0.05 3.2 0.125 1.6 0.062 0.25 \pm 0.05 4.8 0.187 2.4 0.093 0.25 \pm 0.05 6.4 0.250 3.2 0.125 0.30 \pm 0.08 9.5 0.375 4.8 0.187 0.30 \pm 0.08 12.7 0.500 6.4 0.250 0.30 \pm 0.08 19.1 0.750 9.5 0.375 0.43 \pm 0.08

^{**}Wall thickness will be less if tubing recovery is restricted during shrinkage.

Ordering information

Color	Clear
Size selection	Always order the largest size that will shrink snugly over the component being covered.
	Special sizes may be made available upon request.
Standard packaging	On spools
Ordering description	Specify product name, size, and color; for example, RT-375 1/4-X (X=Clear).

Specification values

	Property	Unit	Requirement	Method of test
Physical	Dimensions	mm (inches)	See reverse	ASTM D 2671
	Longitudinal change	percent	+0, –10 maximum	ASTM D 2671
	Tensile strength	psi <i>(MPa)</i>	3500 <i>(24.1)</i> minimum	ASTM D 2671
	Ultimate elongation	percent	300 minimum	ASTM D 2671
	Concentricity (expanded)	percent	70 minimum	AMS-DTL-23053
	Secant modulus (expanded)	psi <i>(MPa)</i>	2.5 x 104 (172) minimum	ASTM D 2671
	Specific gravity		1.90 maximum	ASTM D 2671
	Low-temperature flexibility (4 hours at –55°C/–67°F)		No cracking	AMS-DTL-23053
	Heat shock (4 hours at 250°C/482°F)		No dripping, flowing, or cracking	ASTM D 2671
	Heat resistance (336 hours at 225°C/437°F)			ASTM D 2671
	Followed by test for:	norcont	100 minimum	ACTM D 2471
	Ultimate elongation Clarity stability	percent	100 minimum Marking logible through	ASTM D 2671
	(24 hours at 200°C/392°F)		Marking legible through tubing wall	AMS-DTL-23053
Electrical	Dielectric strength	volts/mil (volt/mm)	400 <i>(15.760)</i> minimum	ASTM D 2671
	Volume resistivity	ohm-cm	10 ¹¹ minimum	ASTM D 2671
	Copper mirror corrosion (16 hours at 160°C/320°F)		Noncorrosive	ASTM D 2671 Procedure A
	Copper contact corrosion		No pitting or blackening	ASTM D 2671
	(16 hours at 160°C/320°F)		of copper	Procedure B
Flamma	Flammability		Self-extinguishing within 1 minute, 25% maximum flag burn	ASTM D 2671 Procedure C
	Fungus resistance Followed by tests for:			ISO 846 Method B
	Tensile strength	psi <i>(MPa)</i>	3500 <i>(24.1)</i> minimum	ASTM D 2671
	Ultimate elongation	percent	300 minimum	ASTM D 2671
	Dielectric strength	volts/mil (volts/mm)	400 <i>(15,760)</i> minimum	ASTM D 2671
Water absorption (24 hours at 23°C/7 Fluid resistance (24 hours at 50°C/1 JP-8 fuel (MIL-T-56. Hydraulic fluid (MIL- Lubricating oil (MIL- Lubricating oil (MIL- 5% NaCl, 0-S-1926 De-icing fluid (MIL- Water Followed by tests for		percent	0.5 maximum	ASTM D 2671
	Fluid resistance (24 hours at 50°C/122°F) in: JP-8 fuel (MIL-T-5624) Hydraulic fluid (MIL-H-5606) Lubricating oil (MIL-L-23699) Lubricating oil (MIL-L-7808) 5% NaCl, 0-S-1926 De-icing fluid (MIL-A-8243)			ASTM D 2671
	-	: (14D-)	2000 (12.0) (-1.0)	ACTA D 0/74
	Tensile strength	psi (MPa)	2000 <i>(13.8)</i> minimum	ASTM D 2671
	Ultimate elongation	percent	250	ASTM D 2671
	Dielectric strength	volts/mil (volts/mm)	400 <i>(15,760)</i> minimum	ASTM D 2671

Note: Consult RT-375 for specific details about test procedures.

Raychem is a trademark of Tyco Electronics Corporation.

Users should independently evaluate the suitability of the product for their application.

Tyco Electronics Corporation 300 Constitution Drive Menlo Park, CA 94025-1164

Tel: (800) 926-2425 (US & Canada) Tel: +1 (650) 361-3860 (All other countries) Faraday Road Dorcan, Swindon, SN3 5HH United Kingdom Tel: +44 1793 528171 3816 Noborito, Tama-ku Kawasaki, Kanagawa 214-8533 Japan Tel: +81 44 900 5102 Asia Pacific Headquarters 26 Ang Mo Kio, Industrial Park 2 Singapore 569507 Tel: +65 4866 151

All information, including illustrations, is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. Tyco Electronics Corporation makes no warranties as to the accuracy or completeness of the information, and disclaims any liability regarding its use. Tyco Electronics Corporation's only obligations are those in the Standard Terms and Conditions of Sale for these products and in no case will Tyco Electronics Corporation be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use, or misuse of the product. Tyco Electronics Corporation's Specifications are subject to change without notice. In addition, Tyco Electronics Corporation reserves the right to make changes in materials or processing without notification to the Buyer which do not affect compliance with any applicable specification.

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

TE Connectivity: