COG Dielectric, 10 – 250 VDC (Commercial Grade)




Overview

KEMET's COG dielectric features a 125°C maximum operating temperature and is considered "stable." The Electronics Components, Assemblies & Materials Association (EIA) characterizes COG dielectric as a Class I material. Components of this classification are temperature compensating and are suited for resonant

circuit applications or those where Q and stability of capacitance characteristics are required. COG exhibits no change in capacitance with respect to time and voltage and boasts a negligible change in capacitance with reference to ambient temperature. Capacitance change is limited to ±30 ppm/°C from -55°C to +125°C.

Benefits

- -55°C to +125°C operating temperature range
- · Lead (Pb)-free, RoHS, and REACH compliant
- EIA 0201, 0402, 0603, 0805, 1206, 1210, 1808, 1812, 1825, 2220, and 2225 case sizes
- DC voltage ratings of 10 V, 16 V, 25 V, 50 V, 100 V, 200 V, and 250 V
- Capacitance offerings ranging from 0.5 pF up to 0.47 μF
- Available capacitance tolerances of ±0.10 pF, ±0.25 pF, ±0.5 pF, ±1%, ±2%, ±5%, ±10%, and ±20%
- · No piezoelectric noise
- Extremely low ESR and ESL
- · High thermal stability
- High ripple current capability



Ordering Information

С	1206	C	104	J	3	G	Α	С	TU
Ceramic	Case Size (L" x W")	Specification/ Series ¹	Capacitance Code (pF)	Capacitance Tolerance ²	Rated Voltage (VDC)	Dielectric	Failure Rate/ Design	Termination Finish ³	Packaging/ Grade (C-Spec)
	0201 0402 0603 0805 1206 1210 1808 1812 1825 2220 2225	C = Standard	Two significant digits + number of zeros. Use 9 for 1.0 - 9.9 pF Use 8 for 0.599 pF e.g., 2.2 pF = 229 e.g., 0.5 pF = 508	B = ±0.10 pF C = ±0.25 pF D = ±0.5 pF F = ±1% G = ±2% J = ±5% K = ±10% M = ±20%	8 = 10 4 = 16 3 = 25 5 = 50 1 = 100 2 = 200 A = 250	G = COG	A = N/A	C = 100% Matte Sn	See "Packaging C-Spec Ordering Options Table" below

¹ Flexible termination option is available. Please see FT-CAP product bulletin C1062_C0G_FT-CAP_SMD

² Additional capacitance tolerance offerings may be available. Contact KEMET for details.

³ Additional termination finish options may be available. Contact KEMET for details.



Packaging C-Spec Ordering Options Table

Packaging Type ¹	Packaging/Grade Ordering Code (C-Spec)
Bulk Bag/Unmarked	Not required (Blank)
7" Reel/Unmarked	TU
13" Reel/Unmarked	7411 (EIA 0603 and smaller case sizes) 7210 (EIA 0805 and larger case sizes)
7" Reel/Unmarked/2 mm pitch²	7081
13" Reel/Unmarked/2 mm pitch ²	7082

¹ Default packaging is "Bulk Bag". An ordering code C-Spec is not required for "Bulk Bag" packaging.

Benefits cont'd

- Preferred capacitance solution at line frequencies and into the MHz range
- No capacitance change with respect to applied rated DC voltage
- Negligible capacitance change with respect to temperature from -55°C to +125°C
- · No capacitance decay with time
- Non-polar device, minimizing installation concerns
- 100% pure matte tin-plated termination finish allowing for excellent solderability
- SnPb plated termination finish option available upon request (5% Pb minimum)

Applications

Typical applications include critical timing, tuning, circuits requiring low loss, circuits with pulse, high current, decoupling, bypass, filtering, transient voltage suppression, blocking and energy storage.

Qualification/Certification

Commercial Grade products are subject to internal qualification. Details regarding test methods and conditions are referenced in Table 4, Performance and Reliability.

Environmental Compliance


Lead (Pb)-free, RoHS, and REACH compliant without exemptions.

¹ The terms "Marked" and "Unmarked" pertain to laser marking option of capacitors. All packaging options labeled as "Unmarked" will contain capacitors that have not been laser marked. The option to laser mark is not available on these devices. For more information see "Capacitor Marking".

² The 2 mm pitch option allows for double the packaging quantity of capacitors on a given reel size. This option is limited to EIA 0603 (1608 metric) case size devices. For more information regarding 2 mm pitch option see "Tape & Reel Packaging Information".



Dimensions - Millimeters (Inches)



EIA Size Code	Metric Size Code	L Length	W Width	T Thickness	B Bandwidth	S Separation Minimum	Mounting Technique
0201	0603	0.60 (0.024) ±0.03 (0.001)	0.30 (0.012) ±0.03 (0.001)		0.15 (0.006) ±0.05 (0.002)	N/A	Solder Reflow
0402	1005	1.00 (0.040) ±0.05 (0.002)	0.50 (0.020) ±0.05 (0.002)		0.30 (0.012) ±0.10 (0.004)	0.30 (0.012)	Only
0603	1608	1.60 (0.063) ±0.15 (0.006)	0.80 (0.032) ±0.15 (0.006)		0.35 (0.014) ±0.15 (0.006)	0.70 (0.028)	
0805	2012	2.00 (0.079) ±0.20 (0.008)	1.25 (0.049) ±0.20 (0.008)		0.50 (0.02) ±0.25 (0.010)	0.75 (0.030)	Solder Wave or Solder Reflow
1206	3216	3.20 (0.126) ±0.20 (0.008)	1.60 (0.063) ±0.20 (0.008)		0.50 (0.02) ±0.25 (0.010)		
1210	3225	3.20 (0.126) ±0.20 (0.008)	2.50 (0.098) ±0.20 (0.008)	See Table 2 for Thickness	0.50 (0.02) ±0.25 (0.010)		
1808	4520	4.70 (0.185) ±0.50 (0.020)	2.00 (0.079) ±0.20 (0.008)		0.60 (0.024) ±0.35 (0.014)		
1812	4532	4.50 (0.177) ±0.30 (0.012)	3.20 (0.126) ±0.30 (0.012)		0.60 (0.024) ±0.35 (0.014)	N/A	Solder Reflow
1825	4564	4.50 (0.177) ±0.30 (0.012)	6.40 (0.252) ±0.40 (0.016)		0.60 (0.024) ±0.35 (0.014)		Only
2220	5650	5.70 (0.224) ±0.40 (0.016)	5.00 (0.197) ±0.40 (0.016)		0.60 (0.024) ±0.35 (0.014)		
2225	5664	5.60 (0.220) ±0.40 (0.016)	6.40 (0.248) ±0.40 (0.016)		0.60 (0.024) ±0.35 (0.014)		



Electrical Parameters/Characteristics

Item	Parameters/Characteristics
Operating Temperature Range	-55°C to +125°C
Capacitance Change with Reference to +25°C and 0 VDC Applied (TCC)	±30 ppm/°C
Aging Rate (Maximum % Capacitance Loss/Decade Hour)	0%
¹ Dielectric Withstanding Voltage (DWV)	250% of rated voltage (5±1 seconds and charge/discharge not exceeding 50 mA)
² Dissipation Factor (DF) Maximum Limit at 25°C	0.1%
³ Insulation Resistance (IR) Limit at 25°C	1,000 megohm microfarads or 100 GΩ (Rated voltage applied for 120±5 seconds at 25°C)

¹DWV is the voltage a capacitor can withstand (survive) for a short period of time. It exceeds the nominal and continuous working voltage of the capacitor.

Capacitance and Dissipation Factor (DF) measured under the following conditions:

Note: When measuring capacitance it is important to ensure the set voltage level is held constant. The HP4284 and Agilent E4980 have a feature known as Automatic Level Control (ALC). The ALC feature should be switched to "ON."

Post Environmental Limits

High Temperature Life, Biased Humidity, Moisture Resistance											
Dielectric	Rated DC Voltage	Capacitance Value	Dissipation Factor (Maximum %)	Capacitance Shift	Insulation Resistance						
COG	All	All	0.5	0.3% or ±0.25 pF	10% of Initial Limit						

² Capacitance and dissipation factor (DF) measured under the following conditions:

¹ MHz \pm 100 kHz and 1.0 Vrms \pm 0.2 V if capacitance \leq 1,000 pF

¹ kHz ±50 Hz and 1.0 Vrms ±0.2 V if capacitance > 1,000 pF

³ To obtain IR limit, divide $M\Omega$ - μ F value by the capacitance and compare to $G\Omega$ limit. Select the lower of the two limits.



Table 1A - Capacitance Range/Selection Waterfall (0201 - 1206 Case Sizes)

	Con	Case Size/ Series	C0201C	CO)402C	C0603C	C0805C	C1206C
Сар	Cap	Voltage Code	8 4 3	8 4 3	5 1 2 A	8 4 3 5 1 2 A	8 4 3 5 1 2 A	8 4 3 5 1 2 A
	Code	Rated Voltage (VDC)	16 16 25	10 16 25	50 100 200 250	10 10 10 100 100 250 250 250	10 16 50 50 200 250	10 16 50 50 100 200 250
		Capacitance Tolerance			Pr	Product Availability and Chip T See Table 2 for Chip Thickne	Thickness Codes	
0.50 & 0.75 pF	508 & 758			BB BB BB	BB		DN DN DN DN DN DN DN	
0.75 pF	758	B C D			BB		DN DN DN DN DN DN DN	
1.0 - 9.1 pF*	109 - 919*	B C D		BB BB BB				EB EB EB EB EB EB
1.1 pF	119	B C D			BB	CF C		
1.2 pF 1.3 pF	129 139	B C D		BB BB BB BB BB BB			DN DN DN DN DN DN DN DN DN DN DN DN DN	EB EB EB EB EB EB EB EB
1.5 pF	159	B C D		BB BB BB				EB EB EB EB EB EB EB
1.6 pF	169	B C D		BB BB BB			DN DN DN DN DN DN DN	
1.8 pF	189	B C D		BB BB BB				EB EB EB EB EB EB
2.0 pF	209	BCD		BB BB BB			DN DN DN DN DN DN DN	
2.2 pF	229	BCD		BB BB BB	BB	CF CF CF CF CF CF CF	DN DN DN DN DN DN DN	EB EB EB EB EB EB
2.4 pF	249	BCD		BB BB BB	BB	CF CF CF CF CF CF CF		EB EB EB EB EB EB
2.7 pF	279	B C D		BB BB BB				EB EB EB EB EB EB
3.0 pF	309	B C D		BB BB BB		CF CF CF CF CF CF CF		
3.3 pF	339	B C D		BB BB BB				EB EB EB EB EB EB
3.6 pF	369	B C D		BB BB BB				EB EB EB EB EB EB
3.9 pF 4.3 pF	399 439	B C D		BB BB BB BB BB BB			DN DN DN DN DN DN DN DN DN DN DN DN DN DN	EB EB EB EB EB EB EB EB
4.7 pF	479	B C D		BB BB BB				EB EB EB EB EB EB
5.1 pF	519	B C D		BB BB BB			DN DN DN DN DN DN DN	
5.6 pF	569	B C D		BB BB BB				EB EB EB EB EB EB
6.2 pF	629	B C D		BB BB BB			DN DN DN DN DN DN	
6.8 pF	689	BCD		BB BB BB	BB	CF CF CF CF CF CF CF	DN DN DN DN DN DN DN	EB EB EB EB EB EB
7.5 pF	759	B C D		BB BB BB	BB	CF CF CF CF CF CF CF	DN DN DN DN DN DN DN	EB EB EB EB EB EB
8.2 pF	829	B C D		BB BB BB	BB	CF CF CF CF CF CF CF	DN DN DN DN DN DN DN	EB EB EB EB EB EB
9.1 pF	919	B C D		BB BB BB			DN DN DN DN DN DN DN	.
10 pF	100		AB¹ AB¹ AB¹					EB EB EB EB EB EB
11 pF	110	F G J K M	A D2 A D2 A D2	BB BB BB				EB EB EB EB EB EB
12 pF 13 pF	120 130	F G J K M	AB ² AB ² AB ²	BB BB BB BB BB BB			DN DN DN DN DN DN DN DN DN DN DN DN DN	EB EB EB EB EB EB EB EB
15 pF	150		AB ² AB ² AB ²					EB EB EB EB EB EB
16 pF	160	F G J K M	אס אס אס	BB BB BB			DN DN DN DN DN DN DN	
18 pF	180		AB ² AB ² AB ²					EB EB EB EB EB EB
20 pF	200	F G J K M		BB BB BB			DN DN DN DN DN DN DN	
22 pF	220	F G J K M	AB ² AB ² AB ²	BB BB BB	BB	CF CF CF CF CF CF CF	DM DM DM DM DN DN DN	EB EB EB EB EB EB
24 pF	240	F G J K M		BB BB BB	BB	CF CF CF CF CF CF CF	DN DN DN DN DN DN DN	EB EB EB EB EB EB
27 pF	270		AB ² AB ² AB ²					EB EB EB EB EB EB
30 pF	300	F G J K M		BB BB BB			DN DN DN DN DN DN DN	
33 pF	330		AB ² AB ² AB ²				DN DN DN DN DN DN DN	
36 pF	360	F G J K M	A D2 A D2 A D2	BB BB BB			DN DN DN DN DN DN DN	
39 pF	390		AB ² AB ² AB ²		BB BB		DN DN DN DN DN DN DN DN DN DN DN DN DN DN	
43 pF 47 pF	430 470	F G J K M	AB ² AB ² AB ²		BB			EB EB EB EB EB EB EB
51 pF	510	F G J K M	אן מאן פר		BB		DN DN DN DN DN DN DN	
56 pF	560		AB ² AB ² AB ²		BB		DN DN DN DN DN DN DN	
62 pF	620	F G J K M	1.5		BB		DN DN DN DN DN DN DN	
68 pF	680		AB ² AB ² AB ²		BB			EB EB EB EB EB EB
75 pF	750	F G J K M		BB BB BB	BB	CF CF CF CF CF CF CF	DN DN DN DN DN DN DN	EB EB EB EB EB EB
82 pF	820	F G J K M	AB ² AB ² AB ²		BB		DN DN DN DN DN DN DN	
91 pF	910	F G J K M		BB BB BB			DN DN DN DN DN DN DN	
100 pF	101	F G J K M			BB BB BB BB			EB EB EB EB EB EB
		Rated Voltage (VDC)	16 16 25	22 2			10 25 25 50 100 200 250	10 25 25 50 100 200 250
Сар	Cap Code	Voltage Code	8 4 3	8 4 3	5 1 2 A	A 8 4 3 5 1 2 A	8 4 3 5 1 2 A	8 4 3 5 1 2 A
	i			 	0402C	C0603C	C0805C	C1206C

^{*}Capacitance range Includes E24 decade values only. (i.e., 10, 11, 12, 13, 15, 16, 18, 20, 22, 24, 27, 30, 33, 36, 39, 43, 47, 51, 56, 62, 68, 75, 82, and 91). xx¹ Available only in D, J, K, M tolerance

These products are protected under US Patents 7,172,985 & 7,670,981, other patents pending, and any foreign counterparts.

 xx^2 Available only in J, K, M tolerance.



Table 1A - Capacitance Range/Selection Waterfall (0201 - 1206 Case Sizes) cont'd

	Con	Case Size/ Series	C0201C		CO	402	C.				C0	60	3C					C0	80	5C					C1	20	6C		
Cap	Cap	Voltage Code	8 4 3	8 4	3	5	1 2	Α	8	4	3	5	1	2	A	8	4	3	5	1	2	Α	8	4	3	5	1	2	Α
	Code	Rated Voltage (VDC)	10 16 25	5 5	25	20	100	250	10	16	25	20	100	200	250	9	16	25	20	100	200	250	10	9	25	20	100	200	250
		Capacitance Tolerance					. , , , ,	Pr	odu See	<u> Tabl</u>	vaila e 2	for (ty a Chip	nd (Th	Chip ickr	Thi less	Dim	ess	sion	les s									
110 - 180 pF*	111 - 181*	F G J K M		BB BI			BB BB		CF				CF									DN						EB	
200 – 270 pF*	201 – 271*	F G J K M		BB BI			BB BB			CF	CF	CF	CF	CF								DN						EB	EB
300 pF 330 pF	301 331	F G J K M F G J K M		BB BI			BB BD BB BD	BD BD		CF CF		CF CF	CF CF	CF CF								DN		EB EB				EB EB	EB EB
360 pF	361	F G J K M				BB I		טט	CF	CF	CF	CF	CF	CF		_				_		DN		_	_	_	EB		EB
390 pF	391	F G J K M		BB BI		BB I			CF	CF	CF	CF	CF	CF					1	1	1	DN			1		EB		
430 pF	431	F G J K M			B BB				CF	CF	CF	CF	CF	CF								DN			1		EB		EB
470 pF	471	F G J K M					BB		CF	CF	CF	CF	CF	CF		DN									1	EB	EB	EB	EB
510 pF	511	F G J K M				BB I			CF	CF	CF	CF	CF	CF								I DN			1	1	EB		EB
560 pF	561	F G J K M		BB BI		_	BB		CF	CF	CF	CF	CF	CF								I DN			_	_	EB	EB	EB
620 pF	621	F G J K M		BB BI			ВВ		CF	CF	CF	CF	CF	CF								DN					EB	EB	EB
680 pF	681	F G J K M		BB BI			BB		CF	CF	CF	CF	CF	CF	CF							I DN					EB	EB	EB
750 pF	751	F G J K M					3B		CF	CF	CF	CF	CF	CF								DN					EB	EB	EB
820 pF	821	F G J K M		вв ві	в ВВ	вв в	3B		CF	CF	CF	CF	CF	CF	CF	DN	DN	DN	DN	DN	DN	DN	EB		EB	EB	EB	EB	EB
910 pF	911	F G J K M		BB BI	B BB	BB I	3B		CF	CF	CF	CF	CF	CF	CF	DN	DN	DN	DN	DP	DP	DP	EB	EB	EB	EB	EB	EB	EB
1,000 pF	102	F G J K M				BB	3B		CF	CF	CF	CF	CF	CF		DN			1	1	1	DP				EB	EB		EB
1,100 pF	112	F G J K M		BB BI					CF	CF	CF	CF	CF	СН		DN			1	1	1	DN				EB	EB		EB
1,200 pF	122	F G J K M		BB BI		BB			CF	CF	CF	CF	CF	СН					1	1		DN			1	1	EB		
1,300 pF	132	F G J K M		BB BI		ВВ			CF	CF	CF	CF	CF	СН		DP		DP	_	_	_	DN			_	_	EC		
1,500 pF	152	F G J K M		BB BI		ВВ			CF	CF	CF	CF	CF	СН	СН			DP				DN					ED	EC	
1,600 pF	162	F G J K M		BB BI					CF	CF	CF	CF	CF	СН	СН			DP	DP			DN					ED	ED	ED
1,800 pF	182	F G J K M		BB BI					CF	CF	CF	CF	CF	CH				DP	DP								ED	ED	ED
2,000 pF	202	F G J K M			B BB				CF	CF	CF	CF	CF			DN						DN					ED	ED	
2,200 pF	222	F G J K M		BB BI	B BB				CF	CF	CF	CF	_	CH	СН	_				_		DN		_	_	_	EE	EE	EE
2,400 pF	242 272	F G J K M							CF CF	CF	CF CF	CF CF	CF CF			DN DN			1	1	1	DN DN			1		EC EC	EC EC	EC EC
2,700 pF 3,000 pF	302								CF	CF CF	CF	CF	CF			DP		DP	DP			DN				1	EC		EB
3,300 pF	332	F G J K M							CF	CF	CF	CF	CF			DP		DP	DP			DN		1		1	EE		EB
3,600 pF	362	F G J K M							CF	CF	CF	CF	CF			DP	DP	DP	DP	DN	1			1			EE	EB	EB
3,900 pF	392	F G J K M							CF	CF	CF	CF	CF			DE		DE	_	DN	_		_	_	_	_	EF	EB	EB
4,300 pF	432	F G J K M							CF	CF	CF	CF	CF			DE	DE	DE		DN			-				EC	EB	EB
4,700 pF	472	F G J K M							CF	CF	CF	CF	CF			DE	DE	DE		DN							EC	EB	EB
5,100 pF	512	F G J K M							CF	CF		CF	•			DE	DE	DE		DN							ED	EB	EB
5,600 pF	562	F G J K M							CF	CF		CF				DN		DN	DN		DP						ED	EB	EB
6,200 pF	622	F G J K M							CF	CF	CF	CF				DN	DN	DN	DN	_	_	_			_	EB	EB		EB
6,800 pF	682	F G J K M							CF	CF	CF	CF				DN	DN	DN	DN	DN	DG	DG	ЕВ	EB	EB	EB	EB	EB	EB
7,500 pF	752	F G J K M							CF	CF	CF					DN	DN	DN	DN	DN	DG	DG	ЕВ	EB	EB	EB	EB	EB	EB
8,200 pF	822	F G J K M							CF	CF	CF					DN	DN	DN	DN	DN	DG	DG	EC	EC	EC	EC	EB	EC	EC
9,100 pF	912	F G J K M							CF	CF	CF					DN			DN	_			EC		EC		EB		EC
10,000 pF	103	F G J K M							CF	CF	CF						DN							ED				EC	
12,000 pF	123	F G J K M							CF	CF	CF					DN							EB				EB	ED	
15,000 pF	153	F G J K M							CF	CF	CF						DN			DG				EB					
18,000 pF	183	F G J K M															DN							EB					
22,000 pF	223	F G J K M															DP		DΕ					EB				EH	EH
27,000 pF	273	F G J K M															DF							EB					
33,000 pF 39,000 pF	333 393	F G J K M F G J K M															DG DG						EC	EB		EE			
47,000 pF	473	F G J K M															DG						EC			EE			
56,000 pF	563	F G J K M														טען	טע	טע					ED				ГП		
68,000 pF	683	F G J K M																						EF					
82,000 pF	823	F G J K M																						EH					
0.10 μF	104	F G J K M																						EH					
		Rated Voltage (VDC)	16 16 25	5 5	25	20	100 200	250	9	16	25	20	9	200	250	2	16	22	20	9	200	250	2	9		_	100	200	250
Сар	Cap Code	Voltage Code	8 4 3	8 4	3	5	1 2	Α	8	4	3	5	1	2	A	8	4	3	5	1	2	Α	8	4	3	5	1	2	A
	-	Case Size/Series	C0201C	<u> </u>	Cu	4020	<u> </u>	-	Π		Cı)603	3C			Ì		CI	080	5C			Ī		C	120	6C		_
	I.	2200 3120, 301103		<u> </u>					Ь_							Щ							ட						

^{*}Capacitance range Includes E24 decade values only. (i.e., 10, 11, 12, 13, 15, 16, 18, 20, 22, 24, 27, 30, 33, 36, 39, 43, 47, 51, 56, 62, 68, 75, 82, and 91). xx¹ Available only in D, J, K, M tolerance

These products are protected under US Patents 7,172,985 & 7,670,981, other patents pending, and any foreign counterparts.

 xx^2 Available only in J, K, M tolerance.



Table 1B - Capacitance Range/Selection Waterfall (1210 - 2225 Case Sizes)

	0.57	Case Size/ Series			C 1	210	C			(C18	080	;	(C18	120	;	(C18	250		(22	20	C	(22	250	
Сар	Cap	Voltage Code	8	4	3	5	1	2	Α	5	1	2	Α	5	1	2	Α	5	1	2	Α	5	1	2	Α	5	1	2	Α
•	Code	Rated Voltage (VDC)	2	16	25	20	100	200	250	20	100	200	250	20	100	200	250	20	100	200	250	20	100	200	250	20	100	200	250
		Capacitance						~	- 7		Proc	uct	Avai	labi	ity a	nd C	hip	Thic	kne	ss C	odes						7		
1.0 - 9.1 pF*	109 - 919*	Tolerance B C D	FB	FB	FB	FB	FB	FB	FB		Se	ета	DIE 2	2 for	Chij	INI	ckn	ess I	Jime	ensic	ons								
10 – 91 pF*	100 - 910*	FGJKM		FB	FB		FB	FB	FB																				
100 – 300 pF*	101 - 301*	F G J K M	FB	FB	FB	FB	FB	FB	FB																				
330 - 430 pF*	331 - 431*	F G J K M		FB	FB	FB	FB	FB	FB	LF	LF	LF	LF																
470 – 910 pF*	471 – 911*	F G J K M		FB	FB	FB	FB	FB	FB	LF	LF	LF	LF	GB	GB	GB	GB												
1,000 pF	102	FGJKM		FB	FB		FB	FB	FB	LF	LF	LF	LF	GB	GB	GB	GB												
1,100 pF 1,200 pF	112 122	F G J K M		FB FB	FB FB		FB FB	FB FB	FB FB	LF LF	LF LF	LF LF	LF LF	GB GB	GB GB	GB GB	GB GB												
1,300 pF	132	F G J K M		FB	FB		FB	FC	FC	LF	LF	LF	LF	GB	GB	GB	GB					l							
1,500 pF	152	FGJKM		FB	FB	FB	FB	FE	FE	LF	LF	LF	LF	GB	GB	GB	GB	İ				i							
1,600 pF	162	FGJKM		FB	FB	FB	FB	FE	FE	LF	LF	LF	LF	GB	GB	GB	GB												
1,800 pF	182	F G J K M		FB	FB	FB	FB	FE	FE	LF	LF	LF	LF	GB	GB	GB	GB												
2,000 pF	202	F G J K M		FB	FB	FB	FC	FE	FE	LF	LF	LF	LF	GB	GB	GB	GB												
2,200 pF	222	F G J K M		FB	FB	FB	FC	FG	FG	LF	LF	LF	LF	GB	GB	GB	GB												
2,400 pF	242	F G J K M		FB	FB	FB	FC	FC	FC	LF LF	LF	LF	LF	OD	OD	OD	OD												
2,700 pF 3,000 pF	272 302	F G J K M		FB FB	FB FB	FB FB	FC FC	FC FF	FC FF	LF	LF LF	LF	LF	GB	GB	GB	GB												
3,300 pF	332	FGJKM		FB	FB		FF	FF	FF	LF	LF			GB	GB	GB	GB												
3,600 pF	362	F G J K M		FB	FB	FB	FF	FF	FF	LF	LF			OD	OB	OD	OD												
3,900 pF	392	FGJKM		FB	FB		FF	FF	FF	LF	LF			GB	GB	GB	GB	НВ	НВ	НВ	НВ								
4,300 pF	432	F G J K M	FB	FB	FB	FB	FF	FF	FF	LF	LF																		
4,700 pF	472	F G J K M	FF	FF	FF	FF	FG	FG	FG	LF	LF			GB	GB	GD	GD	НВ	НВ	НВ	НВ					KE	KE	KE	KE
5,100 pF	512	F G J K M		FB	FB	FB	FG	FG	FG																	KE	KE	KE	KE
5,600 pF	562	F G J K M		FB	FB	FB	FG	FG	FG					GB	GB	GH	GH	НВ	НВ	НВ	НВ					KE	KE	KE	KE
6,200 pF	622	F G J K M		FB	FB		FG	FB	FB					O.D.	OD	0.1	0.1	IIID.	LID	LID	LID	1.5	IF.	I.D.		KE	KE	KE	KE
6,800 pF 7,500 pF	682 752			FB FC	FB FC		FG FC	FB FB	FB FB	ł				GB	GB	GJ	GJ	НВ	НВ	нв	НВ	JE	JE	JB		KE KE	KE	KE KE	KE KE
8,200 pF	822	F G J K M		FC	FC		FC	FB	FB					GB	СН	GB	GB	НВ	НВ	НВ	HR	JE	JE	JB		KE	KE	KE	KE
9,100 pF	912	F G J K M		FE	FE		FE	FB	FB	i				OB	0	0.5	0.5					"-	"-	05		KE	KE	KE	KE
10,000 pF	103	F G J K M		FF	FF	FF	FF	FB	FB	İ				GB	GH	GB	GB	НВ	НВ	HE	HE	JE	JE	JB		KE	KE	KE	KE
12,000 pF	123	F G J K M	FG	FG	FG	FG	FB	FB	FB					GB	GG	GB	GB	НВ	НВ	HE	HE	JE	JE	JB		KE	KE	KE	KE
15,000 pF	153	F G J K M		FG	FG		FB	FC	FC					GB	GB	GB	GB	НВ	НВ			JE	JE	JB		KE	KE	KE	KE
18,000 pF	183	F G J K M		FB	FB	FB	FB	FC	FC					GB	GB	GB	GB	НВ	HE			JE	JE	JB		KE	KE		
22,000 pF	223	F G J K M		FB	FB	FB	FB	FF	FF					GB	GB	GB	GB	НВ	HE			JE	JB	JB		KE	KE		
27,000 pF	273	F G J K M		FB	FB	FB FB	FB	FG FH	FG FH					GB	GB	GB GB	GB GB	НВ	HG			JE JB	JB JB	JB JB		KE	KE		
33,000 pF 39,000 pF	333 393			FB FB	FB FB		FB FE	FH	FH					GB GB	GB GB	GB	GB					JB	JB			NE			
47,000 pF	473	F G J K M		FB	FB		FE	FJ	FJ					GB	GB	GD	GD	l				JB	JB	JB					
56,000 pF	563	F G J K M		FB	FB	FB	FF	-	-					GB	GB	GD	GD	l				JB	JB	JB					
68,000 pF	683	F G J K M	FB	FB	FB		FG							GB	GB	GK	GK					JB	JB	JB					
82,000 pF	823	F G J K M		FC	FC		FH							GB		GM						JB	JB	JB					
0.10 μF	104	FGJKM			FE		FM							GB		GM	GM					JB	JB						
0.12 μF	124	FGJKM	FU		FG										GH GN							JB JB	JB JB						
0.15 μF 0.18 μF	154 184	F G J K M F G J K M	FI	FJ	FH	FIVI								GH	GN							JB JR		JG JG					
0.18 μF 0.22 μF	224	F G J K M	FK	FK	FK									GK								JB		JL					
0.22 μΓ 0.27 μF	274	F G J K M		' '										J.				l				JB	JF			l			
0.33 μF	334	F G J K M	İ															l				JD	JG			l			
0.39 µF	394	F G J K M	l																			JG							
0.47 μF	474	F G J K M	$oxed{igspace}$																	_	_	JG		_		Щ	<u> </u>		
		Rated Voltage (VDC)	2	16			100	200	250	20	100	200		20	100	200	250	20	100	200	250	20	100		250	20	100	200	250
Cap	Cap Code	Voltage Code	8	4	3	5	1	2	A	5	1	2	A	5	1	2	A	5	1	2	A	5	1	2	A	5	1	2	Α
		Case Size/Series		C1210C				C18				C18				C18	25C	7.5	C2220C				C2225C						

^{*}Capacitance range Includes E24 decade values only. (i.e., 10, 11, 12, 13, 15, 16, 18, 20, 22, 24, 27, 30, 33, 36, 39, 43, 47, 51, 56, 62, 68, 75, 82, and 91). These products are protected under US Patents 7,172,985 & 7,670,981, other patents pending, and any foreign counterparts.



Table 2A - Chip Thickness/Tape & Reel Packaging Quantities

Thickness	Case	Thickness ±	Paper 0	uantity ¹	Plastic (Quantity		
Code	Size ¹	Range (mm)	7" Reel	13" Reel	7" Reel	13" Reel		
AB	0201	0.30±0.03	15,000	0	0	0		
BB	0402	0.50±0.05	10,000	50,000	0	0		
BD	0402	0.55±0.05	10,000	50,000	0	0		
CF	0603	0.80±0.07	4,000	15,000	0	0		
CH	0603	0.85±0.07	4,000	10,000	0	0		
DM	0805	0.70±0.20	4,000	15,000	0	0		
DN	0805	0.78±0.10	4,000	15,000	0	0		
DP	0805	0.90±0.10	4,000	15,000	0	0		
DE	0805	1.00±0.10	0	0	2,500	10,000		
DF	0805	1.10±0.10	0	0	2,500	10,000		
DG	0805	1.25±0.15	0	0	2,500	10,000		
EB	1206	0.78±0.10	4,000	10,000	4,000	10,000		
EC	1206	0.90±0.10	0	0	4,000	10,000		
ED	1206	1.00±0.10	0	0	2,500	10,000		
EE	1206	1.10±0.10	0	0	2,500	10,000		
EF	1206	1.20±0.15	0	0	2,500	10,000		
EH	1206	1.60±0.20	0	0	2,000	8,000		
FB	1210	0.78±0.10	0	0	4,000	10,000		
FC	1210	0.90±0.10	0	0	4,000	10,000		
FE	1210	1.00±0.10	0	0	2,500	10,000		
FF	1210	1.10±0.10	0	0	2,500	10,000		
FG	1210	1.25±0.15	0	0	2,500	10,000		
FH	1210	1.55±0.15	0	0	2,000	8,000		
FM	1210	1.70±0.20	0	0	2,000	8,000		
FJ	1210	1.85±0.20	0	0	2,000	8,000		
FK	1210	2.10±0.20	0	0	2,000	8,000		
NC	1706	1.00±0.15	0	0 0	4,000	10,000		
LF GB	1808 1812	1.00±0.15	0 0	0	2,500	10,000		
GD GD	1812	1.00±0.10 1.25±0.15	0	0	1,000 1,000	4,000 4,000		
GH	1812	1.40±0.15	0	0	1,000	4,000		
GG	1812	1.55±0.10	0	0	1,000	4,000		
GK	1812	1.60±0.20	0	0	1,000	4,000		
GJ	1812	1.70±0.15	0	0	1,000	4,000		
GN	1812	1.70±0.13 1.70±0.20	0	0	1,000	4,000		
GM	1812	2.00±0.20	0	0	500	2,000		
HB	1825	1.10±0.15	ő	Ő	1,000	4,000		
HE	1825	1.40±0.15	ő	ő	1,000	4,000		
HG	1825	1.60±0.20	Ŏ	Ö	1,000	4,000		
JB	2220	1.00±0.20	ő	Ő	1,000	4,000		
JD	2220	1.30±0.15	Ö	0	1,000	4,000		
JE	2220	1.40±0.15	Ŏ	ő	1,000	4,000		
JF	2220	1.50±0.15	Ö	Ö	1,000	4,000		
JG	2220	1.70±0.15	0 0		1,000	4,000		
JL	2220	2.00±0.20			500	2,000		
KE	2225	1.40±0.15	0	0	1,000	4,000		
Thickness	Case	Thickness ±	7" Reel	13" Reel	7" Reel 13" Reel			
Code	Size ¹	Range (mm)	Paper Q	uantity ¹	Plastic	Quantity		

Package quantity based on finished chip thickness specifications.

¹ If ordering using the 2 mm Tape and Reel pitch option, the packaging quantity outlined in the table above will be doubled. This option is limited to EIA 0603 (1608 metric) case size devices. For more information regarding 2 mm pitch option see "Tape & Reel Packaging Information".



Table 2B - Bulk Packaging Quantities

Dooksoo	ing Type	Loose P	ackaging							
Раскад	ing Type	Bulk Bag (default)								
Packagi	ng C-Spec ¹	N	/A ²							
Cas	e Size	Packaging Quantities (pieces/unit packaging								
EIA (in)	Metric (mm)	Minimum	Maximum							
0402	1005									
0603	1608									
0805	2012		50,000							
1206	3216									
1210	3225	1								
1808	4520	'								
1812	4532									
1825	4564		20,000							
2220	5650									
2225	5664									

¹ The "Packaging C-Spec" is a 4 to 8 digit code which identifies the packaging type and/or product grade. When ordering, the proper code must be included in the 15th through 22nd character positions of the ordering code. See "Ordering Information" section of this document for further details. Commercial Grade product ordered without a packaging C-Spec will default to our standard "Bulk Bag" packaging. Contact KEMET if you require a bulk bag packaging option for Automotive Grade products.

² A packaging C-Spec (see note 1 above) is not required for "Bulk Bag" packaging (excluding Anti-Static Bulk Bag and Automotive Grade products). The 15th through 22nd character positions of the ordering code should be left blank. All product ordered without a packaging C-Spec will default to our standard "Bulk Bag" packaging.



Table 3 - Chip Capacitor Land Pattern Design Recommendations per IPC-7351


EIA Size Code	Metric Size Code		Maxi	sity Lev mum (I rotrusio)		Media	sity Lev an (Nor otrusio		Density Level C: Minimum (Least) Land Protrusion (mm)							
Code	oode	С	Y	X	V1	V2	С	Y	X	V1	V2	С	Y	X	V1	V2		
0201	0603	0.38	0.56	0.52	1.80	1.00	0.33	0.46	0.42	1.50	0.80	0.28	0.36	0.32	1.20	0.60		
0402	1005	0.50	0.72	0.72	2.20	1.20	0.45	0.62	0.62	1.90	1.00	0.40	0.52	0.52	1.60	0.80		
0603	1608	0.90	1.15	1.10	4.00	2.10	0.80	0.95	1.00	3.10	1.50	0.60	0.75	0.90	2.40	1.20		
0805	2012	1.00	1.35	1.55	4.40	2.60	0.90	1.15	1.45	3.50	2.00	0.75	0.95	1.35	2.80	1.70		
1206	3216	1.60	1.35	1.90	5.60	2.90	1.50	1.15	1.80	4.70	2.30	1.40	0.95	1.70	4.00	2.00		
1210	3225	1.60	1.35	2.80	5.65	3.80	1.50	1.15	2.70	4.70	3.20	1.40	0.95	2.60	4.00	2.90		
1210 ¹	3225	1.50	1.60	2.90	5.60	3.90	1.40	1.40	2.80	4.70	3.30	1.30	1.20	2.70	4.00	3.00		
1808	4520	2.30	1.75	2.30	7.40	3.30	2.20	1.55	2.20	6.50	2.70	2.10	1.35	2.10	5.80	2.40		
1812	4532	2.15	1.60	3.60	6.90	4.60	2.05	1.40	3.50	6.00	4.00	1.95	1.20	3.40	5.30	3.70		
1825	4564	2.15	1.60	6.90	6.90	7.90	2.05	1.40	6.80	6.00	7.30	1.95	1.20	6.70	5.30	7.00		
2220	5650	2.75	1.70	5.50	8.20	6.50	2.65	1.50	5.40	7.30	5.90	2.55	1.30	5.30	6.60	5.60		
2225	5664	2.70	1.70	6.90	8.10	7.90	2.60	1.50	6.80	7.20	7.30	2.50	1.30	6.70	6.50	7.00		

¹ Only for capacitance values ≥ 22 μF

Density Level A: For low-density product applications. Recommended for wave solder applications and provides a wider process window for reflow solder processes. KEMET only recommends wave soldering of EIA 0603, 0805 and 1206 case sizes.

Density Level B: For products with a moderate level of component density. Provides a robust solder attachment condition for reflow solder processes. **Density Level C:** For high component density product applications. Before adapting the minimum land pattern variations the user should perform qualification testing based on the conditions outlined in IPC Standard 7351 (IPC-7351).

Image below based on Density Level B for an EIA 1210 case size.





Soldering Process

Recommended Soldering Technique:

- Solder wave or solder reflow for EIA case sizes 0603, 0805 and 1206
- · All other EIA case sizes are limited to solder reflow only

Recommended Reflow Soldering Profile:

KEMET's families of surface mount multilayer ceramic capacitors (SMD MLCCs) are compatible with wave (single or dual), convection, IR or vapor phase reflow techniques. Preheating of these components is recommended to avoid extreme thermal stress. KEMET's recommended profile conditions for convection and IR reflow reflect the profile conditions of the IPC/ J-STD-020 standard for moisture sensitivity testing. These devices can safely withstand a maximum of three reflow passes at these conditions.

Profile Feature	Terminati	ion Finish
1 Tome Teatare	SnPb	100% Matte Sn
Preheat/Soak		
Temperature Minimum (T _{Smin})	100°C	150°C
Temperature Maximum (T _{Smax})	150°C	200°C
Time (t_s) from T_{smin} to T_{smax}	60 - 120 seconds	60 - 120 seconds
Ramp-Up Rate $(T_L \text{ to } T_P)$	3°C/second maximum	3°C/second maximum
Liquidous Temperature (T_L)	183°C	217°C
Time Above Liquidous (t _L)	60 - 150 seconds	60 - 150 seconds
Peak Temperature (T _P)	235°C	260°C
Time Within 5°C of Maximum Peak Temperature (t _p)	20 seconds maximum	30 seconds maximum
Ramp-Down Rate $(T_p \text{ to } T_L)$	6°C/second maximum	6°C/second maximum
Time 25°C to Peak Temperature	6 minutes maximum	8 minutes maximum

Note 1: All temperatures refer to the center of the package, measured on the capacitor body surface that is facing up during assembly reflow.






Table 4 - Performance & Reliability: Test Methods and Conditions


Stress	Reference	Test or Inspection Method				
Terminal Strength	JIS-C-6429	Appendix 1, Note: Force of 1.8 kg for 60 seconds.				
Board Flex	JIS-C-6429	Appendix 2, Note: Standard termination system – 2.0 mm (minimum) for all except 3 mm for COG. Flexible termination system – 3.0 mm (minimum).				
		Magnification 50 X. Conditions:				
Caldanah ilitu	L CTD 000	a) Method B, 4 hours at 155°C, dry heat at 235°C				
Solderability	J-STD-002	b) Method B at 215°C category 3				
		c) Method D, category 3 at 260°C				
Temperature Cycling	JESD22 Method JA-104	1,000 Cycles (-55°C to +125°C). Measurement at 24 hours +/- 4 hours after test conclusion.				
D: 111 :15	MIL-STD-202 Method 103	Load Humidity: 1,000 hours 85°C/85% RH and rated voltage. Add 100 K ohm resistor. Measurement at 24 hours +/- 4 hours after test conclusion.				
Biased Humidity		Low Volt Humidity: 1,000 hours 85°C/85% RH and 1.5 V. Add 100 K ohm resistor. Measurement at 24 hours +/- 4 hours after test conclusion.				
Moisture Resistance	MIL-STD-202 Method 106	t = 24 hours/cycle. Steps 7a and 7b not required. Measurement at 24 hours +/- 4 hours after test conclusion.				
Thermal Shock	MIL-STD-202 Method 107	-55°C/+125°C. Note: Number of cycles required – 300, maximum transfer time – 20 seconds, dwell time – 15 minutes. Air – Air.				
High Temperature Life	MIL-STD-202 Method 108 /EIA-198	1,000 hours at 125°C (85°C for X5R, Z5U and Y5V) with 2 X rated voltage applied.				
Storage Life	MIL-STD-202 Method 108	150°C, 0 VDC for 1,000 hours.				
Vibration	MIL-STD-202 Method 204	5 g's for 20 minutes, 12 cycles each of 3 orientations. Note: Use 8" X 5" PCB 0.031" thick 7 secure points on one long side and 2 secure points at corners of opposite sides. Parts mounted within 2" from any secure point. Test from 10 – 2,000 Hz				
Mechanical Shock	MIL-STD-202 Method 213	Figure 1 of Method 213, Condition F.				
Resistance to Solvents	MIL-STD-202 Method 215	Add aqueous wash chemical, OKEM Clean or equivalent.				

Storage and Handling

Ceramic chip capacitors should be stored in normal working environments. While the chips themselves are quite robust in other environments, solderability will be degraded by exposure to high temperatures, high humidity, corrosive atmospheres, and long term storage. In addition, packaging materials will be degraded by high temperature—reels may soften or warp and tape peel force may increase. KEMET recommends that maximum storage temperature not exceed 40°C and maximum storage humidity not exceed 70% relative humidity. Temperature fluctuations should be minimized to avoid condensation on the parts and atmospheres should be free of chlorine and sulfur bearing compounds. For optimized solderability chip stock should be used promptly, preferably within 1.5 years of receipt.



Construction



Capacitor Marking (Optional):

Laser marking option is not available on:

- · COG, Ultra Stable X8R and Y5V dielectric devices
- · EIA 0402 case size devices
- EIA 0603 case size devices with Flexible Termination option.
- · KPS Commercial and Automotive grade stacked devices.

These capacitors are supplied unmarked only.



Tape & Reel Packaging Information

KEMET offers multilayer ceramic chip capacitors packaged in 8, 12 and 16 mm tape on 7" and 13" reels in accordance with EIA Standard 481. This packaging system is compatible with all tape-fed automatic pick and place systems. See Table 2 for details on reeling quantities for commercial chips.




Table 5 - Carrier Tape Configuration, Embossed Plastic & Punched Paper (mm)

	Tape	Embosse	ed Plastic	Punched Paper		
EIA Case Size	Size	7" Reel	13" Reel	7" Reel	13" Reel	
	(W)*	Pitch (P ₁)*		Pitch (P ₁)*		
01005 - 0402	8			2	2	
0603	8			2/4	2/4 -	
0805	8	4	4	4	4	
1206 - 1210	8	4	4	4	4	
1805 - 1808	12	4	4			
≥ 1812	12	8	8			
KPS 1210	12	8	8			
KPS 1812 & 2220	16	12	12			
Array 0508 & 0612	8	4	4			

^{*}Refer to Figures 1 & 2 for W and P_1 carrier tape reference locations.

New 2 mm	Pitch Reel	Options*
----------	------------	----------

	Packaging Ordering Code (C-Spec)	Packaging Type/Options
1	C-3190	Automotive grade 7" reel unmarked
١	C-3191	Automotive grade 13" reel unmarked
	C-7081	Commercial grade 7" reel unmarked
	C-7082	Commercial grade 13" reel unmarked

^{* 2} mm pitch reel only available for 0603 EIA case size. 2 mm pitch reel for 0805 EIA case size under development.

Benefits of Changing from 4 mm to 2 mm Pitching Spacing

- · Lower placement costs
- Double the parts on each reel results in fewer reel changes and increased efficiency
- Fewer reels result in lower packaging, shipping and storage costs, reducing waste

^{*}Refer to Tables 6 & 7 for tolerance specifications.



Figure 1 - Embossed (Plastic) Carrier Tape Dimensions




Table 6 – Embossed (Plastic) Carrier Tape Dimensions

Metric will govern

	Constant Dimensions — Millimeters (Inches)									
Tape Size	D_{o}	D ₁ Minimum Note 1	E ₁	P ₀	P ₂	R Reference Note 2	S ₁ Minimum Note 3	T Maximum	T ₁ Maximum	
8 mm	15.010/00	1.0 (0.039)	1.75 ±0.10 (0.069 ±0.004)	4.0 ±0.10 (0.157 ±0.004)	2.0 ±0.05 (0.079 ±0.002)	25.0 (0.984)				
12 mm	1.5 +0.10/-0.0 (0.059 +0.004/-					30 (1.181) 0.600 (0.024)	0.600 (0.024)	0.100 (0.004)		
16 mm	,	(0.059)								
Variable Dimensions — Millimeters (Inches)										
Tape Size	Tape Size Pitch B ₁ Maximum E ₂ F P ₁ T ₂ W Maximum A ₀ , B ₀ & K ₀									
8 mm	Single (4 mm)	4.35 (0.171)	6.25 (0.246)	3.5 ±0.05 (0.138 ±0.002)	4.0 ±0.10 (0.157 ±0.004)	2.5 (0.098)	8.3 (0.327)			
12 mm	Single (4 mm) & Double (8 mm)	8.2 (0.323)	10.25 (0.404)	5.5 ±0.05 (0.217 ±0.002)	8.0 ±0.10 (0.315 ±0.004)	4.6 (0.181)	12.3 (0.484)	Note 5		
16 mm	Triple (12 mm)	12.1 (0.476)	14.25 (0.561)	7.5 ±0.05 (0.138 ±0.002)	12.0 ±0.10 (0.157 ±0.004)	4.6 (0.181)	16.3 (0.642)			

- 1. The embossment hole location shall be measured from the sprocket hole controlling the location of the embossment. Dimensions of embossment location and hole location shall be applied independent of each other.
- 2. The tape with or without components shall pass around R without damage (see Figure 6).
- 3. If S, < 1.0 mm, there may not be enough area for cover tape to be properly applied (see EIA Standard 481 paragraph 4.3 section b).
- 4. B, dimension is a reference dimension for tape feeder clearance only.
- 5. The cavity defined by A_{o} , B_{o} and K_{o} shall surround the component with sufficient clearance that:
 - (a) the component does not protrude above the top surface of the carrier tape.
 - (b) the component can be removed from the cavity in a vertical direction without mechanical restriction, after the top cover tape has been removed.
 - (c) rotation of the component is limited to 20° maximum for 8 and 12 mm tapes and 10° maximum for 16 mm tapes (see Figure 3).
 - (d) lateral movement of the component is restricted to 0.5 mm maximum for 8 and 12 mm wide tape and to 1.0 mm maximum for 16 mm tape (see Figure 4).
 - (e) for KPS Series product, A, and B, are measured on a plane 0.3 mm above the bottom of the pocket.
 - (f) see Addendum in EIA Standard 481 for standards relating to more precise taping requirements.



Figure 2 - Punched (Paper) Carrier Tape Dimensions




Table 7 - Punched (Paper) Carrier Tape Dimensions

Metric will govern

Constant Dimensions — Millimeters (Inches)									
Tape Size	Tape Size D_0 E_1 P_0 P_2 T_1 Maximum						R Reference Note 2		
8 mm	1.5 +0.10 -0.0 (0.059 +0.004 -0.0)	1.75 ±0.10 (0.069 ±0.004)	4.0 ±0.10 (0.157 ±0.004)	2.0 ±0.05 (0.079 ±0.002)	0.10 (0.004) Maximum	0.75 (0.030)	25 (0.984)		
Variable Dimensions — Millimeters (Inches)									
Tape Size	Tape Size Pitch E2 Minimum F P ₁ T Maximum W Maximum A ₀ B ₀								
8 mm	Half (2 mm)	6.25	3.5 ±0.05	2.0 ±0.05 (0.079 ±0.002)	1.1	8.3 (0.327)	Note 1		
8 mm	Single (4 mm)	(0.246)	(0.138 ±0.002)	4.0 ±0.10 (0.157 ±0.004)	(0.098)	8.3 (0.327)	Note i		

- 1. The cavity defined by A_{n} , B_{n} and T shall surround the component with sufficient clearance that:
 - a) the component does not protrude beyond either surface of the carrier tape.
 - b) the component can be removed from the cavity in a vertical direction without mechanical restriction, after the top cover tape has been removed.
 - c) rotation of the component is limited to 20° maximum (see Figure 3).
 - d) lateral movement of the component is restricted to 0.5 mm maximum (see Figure 4).
 - e) see Addendum in EIA Standard 481 for standards relating to more precise taping requirements.
- 2. The tape with or without components shall pass around R without damage (see Figure 6).



Packaging Information Performance Notes

1. Cover Tape Break Force: 1.0 Kg minimum.

2. Cover Tape Peel Strength: The total peel strength of the cover tape from the carrier tape shall be:

Tape Width	Peel Strength		
8 mm	0.1 to 1.0 Newton (10 to 100 gf)		
12 and 16 mm	0.1 to 1.3 Newton (10 to 130 gf)		

The direction of the pull shall be opposite the direction of the carrier tape travel. The pull angle of the carrier tape shall be 165° to 180° from the plane of the carrier tape. During peeling, the carrier and/or cover tape shall be pulled at a velocity of 300 ±10 mm/minute.

3. Labeling: Bar code labeling (standard or custom) shall be on the side of the reel opposite the sprocket holes. *Refer to EIA Standards 556 and 624*.

Figure 3 - Maximum Component Rotation




Figure 4 - Maximum Lateral Movement




Figure 5 - Bending Radius







Figure 6 - Reel Dimensions



Note: Drive spokes optional; if used, dimensions B and D shall apply.

Table 8 - Reel Dimensions

Metric will govern

Constant Dimensions — Millimeters (Inches)									
Tape Size	A	B Minimum	С	D Minimum					
8 mm	178 ±0.20	1.5 (0.059)	13.0 +0.5/-0.2 (0.521 +0.02/-0.008)	20.2 (0.795)					
12 mm	(7.008 ±0.008) or								
16 mm	330 ±0.20 (13.000 ±0.008)	,	,						
	Variable Dimensions — Millimeters (Inches)								
Tape Size	N Minimum	W_{1}	W ₂ Maximum	W ₃					
8 mm		8.4 +1.5/-0.0 (0.331 +0.059/-0.0)	14.4 (0.567)						
12 mm	50 (1.969)	12.4 +2.0/-0.0 (0.488 +0.078/-0.0)	18.4 (0.724)	Shall accommodate tape width without interference					
16 mm		16.4 +2.0/-0.0 (0.646 +0.078/-0.0)	22.4 (0.882)						



Figure 7 - Tape Leader & Trailer Dimensions





Figure 8 – Maximum Camber





KEMET Electronic Corporation Sales Offices

For a complete list of our global sales offices, please visit www.kemet.com/sales.

Disclaimer

All product specifications, statements, information and data (collectively, the "Information") in this datasheet are subject to change. The customer is responsible for checking and verifying the extent to which the Information contained in this publication is applicable to an order at the time the order is placed.

All Information given herein is believed to be accurate and reliable, but it is presented without guarantee, warranty, or responsibility of any kind, expressed or implied.

Statements of suitability for certain applications are based on KEMET Electronics Corporation's ("KEMET") knowledge of typical operating conditions for such applications, but are not intended to constitute – and KEMET specifically disclaims – any warranty concerning suitability for a specific customer application or use. The Information is intended for use only by customers who have the requisite experience and capability to determine the correct products for their application. Any technical advice inferred from this Information or otherwise provided by KEMET with reference to the use of KEMET's products is given gratis, and KEMET assumes no obligation or liability for the advice given or results obtained.

Although KEMET designs and manufactures its products to the most stringent quality and safety standards, given the current state of the art, isolated component failures may still occur. Accordingly, customer applications which require a high degree of reliability or safety should employ suitable designs or other safeguards (such as installation of protective circuitry or redundancies) in order to ensure that the failure of an electrical component does not result in a risk of personal injury or property damage.

Although all product-related warnings, cautions and notes must be observed, the customer should not assume that all safety measures are indicted or that other measures may not be required.

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

KEMET:

```
C0805C300K1GACTU C0603C339D3GACTU C0603C751F8GACTU C0603C758C1GACTU C0603C910J1GACTU
C0805C160G5GACTU C0805C271J3GACTU C0805C109B3GACTU C0805C439B5GACTU C0805C759B5GACTU
C0805C129B1GACTU C0603C629B3GACTU C0603C180F1GACTU C0603C100B5GACTU
C0603C181F5GAC7411 C0603C202F5GACTU C0603H103F3GAC7130 C0805C201F3GACTU
C0603C151G1GACTU C0805C221G4GACTM C0805C300G5GACTM C0805C309C5GACTM C0805C339D5GACTM
C0805C390J1GACTM C0805C391F5GACTM C0805C439D1GACTM C0805C560K5GACTM
C1206C102J1GACTM C1206C109C5GACTM C1206C120D5GACTM C1206C121J1GACTM C1206C152J1GACTM
C1206C180J1GACTM C1206C220J1GACTM C1206C220K5GACTM C1206C221J5GACTM C1206C270K5GACTM
C1206C271J5GACTM C1206C272J5GACTM C1206C279C5GACTM C1206C301K5GACTM C1206C330J2GACTM
C1206C390D5GACTM C1206C472F5GACTM C1206C560F5GACTM C1206C560J1GACTM C1206C561J1GACTM
C1206C569J1GACTM C1206C681K5GACTM C1206C689J5GACTM C1206C820F5GACTM C1206C821K5GACTM
C1210C103G5GACTM C1210C122F1GACTM C1210C391J5GACTM C1210C682K1GACTM C1812C103J5GACTM
C0805C209C5GACTM C0805C221G5GACTM C0805C221K5GACTM C0805C270K1GACTM
C0805C821F5GACTM C1206C100K1GACTM C1206C102J5GACTM C1206C120J5GACTM C1206C121J5GACTM
C1206C122J1GACTM C1206C151G5GACTM C1206C220G5GACTM C1206C220K1GACTM
C1206C221F5GACTM C1206C221K1GACTM C1206C229D5GACTM C1206C332J1GACTM C1206C391J5GACTM
C1206C391K5GACTM C1206C471J1GACTM C1206C471J2GACTM C1206C471J5GACTM C1206C510J5GACTM
C1206C519C5GACTM C1206C569C5GACTM C1206C569D5GACTM C1206C680J1GACTM C1206C680J5GACTM
C1210C123F5GACTM C1210C330J1GACTM C1812C152J5GACTM C0805C101J5GAC7025 C0805C471J1GAC
```