

RW-2500/1 Revision 4 Page 1 of 6 September 2014

Specification RW-2500/1

TE 108-121004

HIGH TEMPERATURE HEAT SHRINK IDENTIFICATION MARKER SLEEVES - HTMS (HTTMS)

Approved Signatories:

This document is electronically reviewed and approved by TE Connectivity.



RW-2500/1 Revision 4 Page 2 of 6 September 2014

1. REVISION HISTORY

Revision Number	Description of change	Date	Incorporated By
1	AFC 256	14/04/04	Alan Kean
2	AFC 403	13/02/06	John Swift
3	AFC 421	17/07/06	Gordon White and Steve Rowland
4	Refer to PCN	24/09/14	Lee Smith

2. SCOPE

This specification sheet, when used with RW-2500, defines the product characteristics and performance of TE Connectivity High Temperature Heat Shrink Identification Marker Sleeves.

The IBM daisy wheel printer and ink cartridge developed for HTMS is now obsolete. TE can only guarantee the performance properties covered in this standard, and not any marking applied using non-recommended printing systems. Where non-standard systems are used, customers are required to carry out their own validation testing.

This system is not recommended where strain relief properties are required. Product is available in 2:1 shrink ratio.

Unless specified, the tube size for qualification testing is 6.4mm (1/4 inch).

3. REQUIREMENTS

3.1. MATERIAL

The sleeving shall be fabricated from irradiated, thermally stabilized, modified polyvinylidene fluoride compound. It shall be homogeneous and essentially free from flaws, defects, pinholes, bubbles, seams, cracks or inclusions.

3.2. COLOR

The sleeves shall be supplied in white, unless otherwise specified.

3.3. PROPERTIES

The sleeves shall meet the requirements of Table 3.

3.4. FORM

The sleeves shall be cut lengths in accordance with Table 1.



RW-2500/1 Revision 4 Page 3 of 6 September 2014




Figure 1: HTMS System 90 Assembly



RW-2500/1 Revision 4 Page 4 of 6 September 2014

TABLE 1 Dimensions

USA DESCRIPTIONS

	As Supplied			Recovered				
Product Description	Inside Diameter Minimum		Marking Length Minimum		Inside Diameter Maximum		Wall Thickness	
	in.	mm.	in.	mm.	in.	mm.	in.	mm.
HTTMS-3/32-1.50	0.093	2.36	1.50	39.41	0.031	0.79	0.016 + 0.003	0.41+0.08
HTTMS-1/8-1.50	0.125	3.17	1.50	39.41	0.062	1.57	0.013 + 0.003	0.33+0.08
HTTMS-3/16-1.50	0.187	4.74	1.50	39.41	0.093	2.36	0.015 + 0.003	0.38+0.08
HTTMS-1/4-1.50	0.250	6.35	1.50	39.41	0.125	3.17	0.015 + 0.003	0.38+0.08
HTTMS-3/8-1.50	0.375	9.50	1.50	39.41	0.187	4.74	0.015 + 0.003	0.38+0.08
HTTMS-1/2-1.50	0.475	12.07	1.50	39.41	0.250	6.35	0.015 + 0.003	0.38+0.08
HTTMS-3/4-1.50	N/A	N/A	1.50	39.41	0.375	9.53	0.017 + 0.003	0.43+0.08
HTTMS-3/32-1.75	0.093	2.36	1.75	44.45	0.031	0.79	0.016 + 0.003	0.41+0.08
HTTMS-1/8-1.75	0.125	3.17	1.75	44.45	0.062	1.57	0.013 + 0.003	0.33+0.08
HTTMS-3/16-1.75	0.187	4.74	1.75	44.45	0.093	2.36	0.015 + 0.003	0.38+0.08
HTTMS-1/4-1.75	0.250	6.35	1.75	44.45	0.125	3.17	0.015 + 0.003	0.38+0.08
HTTMS-3/8-1.75	0.375	9.50	1.75	44.45	0.187	4.74	0.015 + 0.003	0.38+0.08
HTTMS-3/4-1.75	N/A	N/A	1.75	44.45	0.375	9.53	0.017 + 0.003	0.43+0.08

EUROPEAN DESCRIPTIONS

		As Supplied				Recovered			
Product Description	Inside Diameter Minimum		Marking Length Minimum		Inside Diameter Maximum		Wall Thickness		
	in.	mm.	in.	mm.	in.	mm.	in.	mm.	
HTMS-3/32	0.093	2.36	1.89	48	0.031	0.79	0.016 + 0.003	0.41+0.08	
HTMS-1/8	0.125	3.17	1.89	48	0.062	1.57	0.013 + 0.003	0.33+0.08	
HTMS-3/16	0.187	4.74	1.89	48	0.093	2.36	0.015 + 0.003	0.38+0.08	
HTMS-1/4	0.250	6.35	1.89	48	0.125	3.17	0.015 + 0.003	0.38+0.08	
HTMS (HTTMS)-3/8	0.375	9.50	1.85	47	0.187	4.74	0.015 + 0.003	0.38+0.08	
HTMS (HTTMS)-1/2	0.475	12.07	1.81	46	0.250	6.35	0.015 + 0.003	0.38+0.08	
HTMS (HTTMS)-3/4	N/A	N/A	1.65	42	0.375	9.53	0.017 + 0.003	0.43+0.08	

TABLE 2

Mandrel Dimensions for Heat Shock, Heat Aging and Low Temperature Flexibility

Tubing Sizo	Mandrel Diameter		
Tubing Size	in	mm	
3/32 through 3/16	5/16	7.9	
1/4 through 3/4	3/4	19.0	



RW-2500/1 Revision 4 Page 5 of 6 September 2014

TABLE 3 Requirements

TABLE 3 Requirements								
PROPERTY	UNIT	REQUIREMENT	RW-2500 TEST METHOD					
PHYSICAL	mm (inches)	In accordance with Table 1						
Dimensions	mm (inches)	in accordance with rable i	RW-2500 Section 4.3.1.1					
Dimensional Recovery	mm (inches)	In accordance with Table 1						
3 minutes at 200°C (392°F)	()	door dance	A OTM D 0074					
Longitudinal Change 3 minutes at 200°C (392°F)	Percent	10 maximum	ASTM D 2671					
Tensile Strength	MPa (psi)	34.5 (5000) minimum	RW-2500 Section 4.3.2.1 ASTM D 2671					
Ultimate Elongation	Percent	200 minimum	2 inches/minute					
Specific Gravity		1.8 maximum	RW-2500 Section 4.3.3 ASTM D 2671					
Low Temperature Flexibility			RW-2500 Section					
4 hours at -55°C (-67°F)		No cracking	4.3.5.1					
Heat Shock			RW-2500 Section					
4 hours at 275°C (527°F)		No dripping, flowing, or cracking	4.3.6.1					
Heat Aging			RW-2500 Section					
168 hours at 225°C (437°F)		No cracking	4.3.7.1					
Copper Contact Corrosion			RW-2500 Section					
16 hours at 150° C (302°F)		No pitting or blackening of core	4.3.14.1					
Pull-Off Force	N (5 1)	20 (5.0)	RW-2500 Section					
Size: 3/32 through 1/8	N (Pounds)	22 (5.0) maximum						
Size: 3/16 through 1/4	N (Pounds)	31 (7.0) maximum	4.3.8					
Size: 3/8 through 3/4	N (Pounds)	44 (10.0) maximum						
Vacuum Outgassing			RW-2500 Section					
TML (Total Mass Loss)	Percent	1.0 maximum	4.3.18					
VCM (Volatile Condensable Material)	Percent	0.1 maximum	ASTM E 595					
Temperature Cycling	reiceni	U. i maximum						
6 cycles of:								
0.5 hr/-196°C (-321° F)			RW-2500 Section 4.3.23					
0.5 hr/200°C (392° F)		No cracking						
ELECTRICAL		i to ordorung						
Dielectric Strength			RW-2500 Section					
Size: 3/32 through 3/16		31.5 (800) minimum	4.3.11.1					
1/4 through 1/2	kV/mm (V/mil)	23.6 (600) minimum	ASTM D 2671					
	,	, ,	RW-2500 Section					
Volume Resistivity	ohm-cm	10 ¹² minimum	4.3.12.1 ASTM D 2671					
CHEMICAL			RW-2500 Section					
Corrosive Effect		Non Corrosive	4.3.13.1					
16 hours at 150°C (302°F)			ASTM D 2671					
Flammability								
UL 224		Pass VW-1	RW-2500 Section					
ASTM D 876 Average time of burning	Seconds	15 maximum	4.3.15.1 and					
			Section 4.3.15.2					
Fungus Resistance		Rating of 1 or less	ASTM G 21					



RW-2500/1 Revision 4 Page 6 of 6 September 2014

Additional notes for Low Temperature Flexibility

For sizes smaller than 1/4 inch, recover three 6-inch long specimens and cool to room temperature.

For sizes 1/4 inch and larger, prepare test strips as follows: Recover three 6-inch long sections of tubing, and while they are still hot, slit longitudinally, and flatten between metal plates. Cool to room temperature, remove metal plates, and cut into 1/4-inch wide strips.

Place the specimens in a cold chamber with the mandrel specified in Table 2 at -55°C (-67°F) for 4 hours. While still in the cold chamber, and at this same temperature, wrap the specimens around the mandrel not less than 360° in approximately 2 seconds.

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

TE Connectivity:

<u>HTTMS-CM-1/2-4H-4</u> <u>HTMS-1/4-9</u> <u>HTTMS-CM-1/4-4H-9-CS7415</u> <u>HTTMS-3/16-1.50-9</u> <u>HTTMS-1/4-1.75-9</u> <u>HTTMS-3/8-1.75-9</u> HTMS-3/8-1.75-9 HTMS-3/8-9 HTMS-3/8-1.75-4