

### **Product Data Sheet**

Updated : July 1999 Supersedes : January 1995

#### **Product Description**

Physical Properties Not for specification purposes High Peel Moderate Shear Pressure Sensitive SJ3530 (Hook) SJ3531 (Loop) 3M Scotchmate hook and loop fasteners described here consist of two woven strips, one of which is covered with tiny stiff hooks and the other with pliable loops. Pressed together they fasten; to open simply pull apart. Scotchmate hook and loop fasteners are coated on the backside with a pressure sensitive adhesive. This allows the products to be used in typical hook and loop fastening applications while adhering to a variety of different surfaces.

Adhesive Type		3M ref :		
Width (mm)	19 mm 25 mm 38 mm 50 mm			
Release Liner	Yellow Polypropylene			
Colours	Black, White			
Shelf Life		12 months from date of despatch by 3M when stored in the original carton at 21°C (70°F) & 50% Relative Humidity		

Performance Characteristics Not for specification purposes	Temperature Performance Continuous Intermittent	-29° to 43°C -29° to 49°C	When used for static load applications, temperatures should not exceed 43°C.

Date : July 1999 Hook & Loop Fastening System SJ3530 (Hook) & SJ3531 (Loop)

# Backing/Substrate Selection

3M Scotchmate Fasteners provide a firm adhesive bond to a wide variety of surfaces, including (under most conditions) the following:

\*Note: some plasticisers on plasticised vinyl have an adverse effect on the strength of the adhesive bond of the fastener over time.

SUBSTRATES	PRESSURE-SENSITIVE ADHESIVE-BACKED
Base Metal	$\checkmark$
Painted Metal	$\checkmark$
Finished Wood	$\checkmark$
Plastics : Polystyrene	$\checkmark$
Acrylic	✓
Polyethylene	$\checkmark$
Polypropylene	$\checkmark$
Polycarbonate	$\checkmark$
Rigid Vinyl	$\checkmark$
Plasticised Vinyl	√ *
Paper, cardboard	$\checkmark$
Glass	$\checkmark$

Application Information	Press Bonding :	Typical Press Bonding :	
	May be bonded to fabrics** 1.6mm utilising heat and, or pressure. Heat through	Bonding Temperature : 121°C to 218°C	
	<ul> <li>**Note: 3M Scotchmate</li> <li>fasteners are washable but</li> <li>not drycleanable.</li> </ul>	Bonding Pressure : 210 to 690 kPa	
		Bonding Time : 3 to 30 seconds.	
Application Techniques	Pressure Sensitive Attachment:	(Note: When using solvents, be sure to follow the	Minimum Dwell Time :
	Adhesive backed 3M Scotchmate fasteners should be applied above 20°C to surfaces that are smooth, dry and free of oils or mould release agents. It	manufacturer's precautions and directions for use.) With firm roller pressure, apply the fastener allowing an appropriate dwell time at room temperature before	1 hour.
	is recommended to wipe the substrate with an isopropanol/water solution	loading or disengaging. Do not touch adhesive after liner is removed. To	Recommended Dwell Time :
	(50/50) or with Heptane and allow to dry.	increase resistance to edge lifting, round the corners or recess product into substrate.	24 hours.

			Hook & Loop Fastening System SJ3530 (Hook) & SJ3531 (Loop)	
Closure Performance Characteristics	3M Scotchmate hook and loop fasteners derive their strength from the area of engagement as well as closure pressure.	Vibration or side to side movement tends to increase closure performance. The properties shown here are measured under defined laboratory conditions (50% R.H., 21°C).	Tests are desig maximum relia Closure charac indicated by bo and typical valu	bility. cteristics are oth minimum
		<u>Closure Performance at</u> 21°C and 50% R.H.	<u>Minimum</u>	<u>Typical</u>
		Dynamic Shear <sup>a</sup> (kPa)	55	97
		Dynamic Tensile <sup>b</sup> (kPa)	21	31
		Lengthwise peel (N/100mm)	18	33
		Overlap Shear: Overlapping 3M Scotchmate Hook and Loop around a curved surface significantly increases shear strength.		
		a. Hook and Loop products are engaged with firm pressure and disengaged at a separation rate of 305mm/min.	<sup>b.</sup> Tested on r	igid surfaces.

Date : July 1999

Date : July 1999 Hook & Loop Fastening System SJ3530 (Hook) & SJ3531 (Loop)

### **Additional Information**

Scotchmate fastening systems are 100% Nylon. They are pre-shrunk to ensure maximum dimensional stability and flatness. The loop surface is napped for maximum engagement strength and reclosure life.

3M and Scotchmate are trademarks of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications.

This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.



#### **Tapes & Adhesives**

3M United Kingdom PLC 3M House, 28 Great Jackson Street, Manchester, M15 4PA Customer Service :

Tel [3MUKP1]0161 236 8500 Fax 0161 237 1105 3M Ireland 3M House, Adelphi Centre, Upper Georges Street, Dun Laoghaire,Co. Dublin, Ireland © 3M United Kingdom PLC 1996

Customer Service :

Tel (01) 280 3555 Fax (01) 280 3509 Page: 4 [3MUKP1]

## **Mouser Electronics**

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

**3M**:

SJ3531(BLK)3/4"X50YDS SJ3530(BLK)3/4"X50YDS