

Raychem

Specification RT-1050/1
This Issue: Issue 2
Date: February 26, 1997
Replaces: Issue 1

THERMOFIT® ADHESIVE AND SEALANT THERMOFIT S-1017

Thermofit S-1017 thermoplastic adhesive was developed for use with Thermofit heat-shrinkable products where the molded part or tubing is precoated with adhesive on the bonding area. This adhesive is tough and flexible and bonds to polyolefins, vinyls, neoprene, lead, and many other metals such as steel and aluminum.

| PROPERTY | UNIT | REQUIREMENT | METHOD OF TEST |
|-------------------------------|-------------------|---------------------|---------------------|
| PHYSICAL | | | |
| Visual | | Pass | Section 4.3.1.1 |
| Specific Gravity | | $0.95 \pm .05$ | Section 4.3.1.2 |
| | | | ASTM D 792 |
| Viscosity, at 191° C | centiposie | 9000 ± 3000 | Section 4.3.1.3.2 |
| | | | ASTM D 1084 |
| | | | Method B |
| Softening Point | C | 120 ± 10 | E28 |
| Low Temperature Impact | C | -20 max | 4.3.1.7, ASTM D 746 |
| Brittleness | | | |
| Blocking (Cohesive @ 55° C) | | Pass | 4.3.1.8 |
| 2 | | | ASTM D 1146 |
| Adhesive Peel* | Pounds/inch width | | Section 4.3.1.9 |
| Polyethylene | | 20 minimum | |
| Lead | | 5 minimum | |
| Neoprene | | 10 minimum | |
| PVC | | 30 minimum | |
| Steel | | 15 minimum | |
| CHEMICAL | | | |
| Water Absorption | Percent | 1.0 maximum | Section 4.3.2.1 |
| | | | ASTM D 570 |
| Corrosive Effect | | Pass | Section 4.3.2.2 |
| 16 hours at 121° C (250° F) | | | ASTM D 2671 |
| | | | Method B |
| Environmental Stress-Cracking | | Pass | Section 4.3.2.3 |
| 48 hours at 50° C | | | ASTM D 1693 |
| Environmental Stress-Cracking | | Pass | Section 4.3.2.4 |
| of Substrate | | | ASTM D 1693 |
| 30 days at 50° C | | | |
| Fungus Resistance | | Rating of 1 or less | Section 4.3.2.5 |
| | | | ASTM G 21 |

| Solvent and Fluid Resistance Weight change after 24 hours at 23° C (74° F): Detergent Solution (#12) Hydraulic Fluid (MIL-H-5606) Lube Oil (Mil-L-7808) ASTM Oil (#49) | Percent | 3 maximum 10 maximum 5 maximum 15 maximum | Section 4.3.2.6 ASTM D 543 |
|--|-----------|---|---|
| ELECTRICAL Volume Resistivity | ohm-cm | 10 ¹⁰ min | Section 4.3.3.1 |
| Dielectric Strength | volts/mil | 500 min | ASTM D 257 Section 4.3.3.2 ASTM D 149 |

Molding temperature for 4.2.1.1 shall be 149° C ($300~^{\circ}F$). Acceptance Tests: Visual, Viscosity, Peel (Steel)

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

TE Connectivity: S1017-1.0X50-CS8192