

86750 Nickel/Copper Fabric Tape

Innovative **Technology** for a **Connected** World



NI/CU POLYESTER CONDUCTIVE FABRIC TAPE

Laird Technologies' Conductive Fabric Tape 86750 product is made of metallized fabric (polyester Ni/Cu) coated with a pressure sensitive adhesive. These products can be used as EMI/RFI shielding and grounding tape, which would meet market requirements.

FEATURES ✓RoHS

- RoHS compliant
- Halogen-free per IEC-61249-2-21 standard
- Low surface resistivity of < 0.03 Ω/□ provides excellent conductivity
- Shielding effectiveness of 70 dB across a wide spectrum of frequencies

MARKETS



- Cabinet applications
- LCD and Plasma TV
- Medical equipment
- Servers
- Printers
- Laptop computers

global solutions: local support ™

USA: +1.866.928.8181 Europe: +49.0.8031.2460.0 Asia: +86.755.2714.1166




Innovative **Technology** for a **Connected** World

86750 Nickel/Copper Fabric Tape

Item	Unit	Value	Test Method
Thickness	mm	$0.075 \text{ mm} \pm 0.015$	-
Peel Adhesion	Kgf / 25 mm	>0.9	PSTC 101*
Shear Adhesion			ASTM D4935
at R.T.	Hrs	>72	PSTC 107#
at 80°C	Hrs	>3	PSTC 107#
Tensile Strength	Kgf / 25 mm	>7.5	
Operation Temperature	°C	0-80	
Surface Resistivity (Fabric Side)	Ω/□	<0.03	ASTM F390
Z-axial Resistance	Ω	<0.03	
Shielding Effectiveness+			ASTM D4935
at 100 MHz	dB	70	
at 1 GHz	dB	75	
Package Dimensions (Max. Width: 1000 mm)	M	W: Dimension by Customer Spec L: Standard Length of 20 M	
Shelf Life (Under 23°C/65% R.H.)		Six Months	

^{*:}Test Method A, dwell time 30 min. #:Contact area 25 mm by 25 mm +:Typical value

COMPOSITION OF PRODUCT



APPLICATION TECHNIQUES

- 1. Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure develops better adhesive contact & thus improves bond strength.
- To obtain optimum adhesion, the bonding surfaces must be clean, dry and well unified. A typical surface cleaning solvent is isopropyl alcohol. Use proper safety precautions for handling solvents.
- 3. Ideal tape application temperature range is 21°C to 38°C. Initial tape application to surfaces at temperatures below 10°C is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

Laird:

46X7502520.NN00 46X7501920.NN00 46X7501320.NN00