SPECIFICATION CONTROL DRAWING

55A8039

Treated to prevent fraying.

WIRE, RADIATION-CROSSLINKED, MODIFIED ETFE-INSULATED, NORMAL WEIGHT, GENERAL PURPOSE, 600 VOLT


Date 10-31-17

Revision

This specification sheet forms a part of the latest issue of Raychem Specification 55A.

PRIMARY INSULATION - RADIATION-CROSSLINKED, MODIFIED ETFE

Primary insulation shall be of a contrasting pigmentation to that of the jacket.



JACKET - RADIATION-CROSSLINKED, MODIFIED ETFE

TABLE I. CONSTRUCTION DETAILS										
	WIRE SIZE (AWG)	CONDUCTOR STRANDING (number x AWG)	DIAMETER OF STRANDED CONDUCTOR (inch)		FINISHED WIRE					
PART NUMBER <u>1</u> /					MAXIMUM RESISTANCE AT 20°C	DIAMETER (inch)	MAXIMUM WEIGHT			
-			MINIMUM	MAXIMUM	(ohms/1000 ft.)	(,	(lbs/1000 ft.)			
55A8039-8-*	8	133 x 29	.158	.173	.701	.225 ± .014	64.9			
55A8039-6-*	6	133 x 27	.198	.217	.445	.267 ± .015	98.3			
55A8039-4-*	4	133 x 25	.250	.274	.280	.325 ± .015	155.			
55A8039-2-*	2	665 x 30	.320	.340	.183	.405 ± .016	239.			
55A8039-1-*	1	817 x 30	.360	.380	.149	.445 ± .016	290.			
55A8039-0-*	0	1045 x 30	.395	.425	.116	.485 ± .016	377.			
55A8039-00-*	00	1330 x 30	.440	.475	.091	.545 ± .016	487.			
55A8039-000-*	000	1665 x 30	.500	.540	.071	.625 ± .022	603.			
55A8039-0000-*	0000	2109 x 30	.565	.605	.056	.690 ± .022	740.			

TABLE II. PERFORMANCE DETAILS								
PART NUMBER <u>1</u> /	MANDREL DIAMETE (inch) (± 3%)	R	WEIGHT (lb) (± 3%)					
	IMMERSION, LIFE CYCLE, AND ACCELERATED AGING	COLD BEND	IMMERSION, LIFE CYCLE, AND ACCELERATED AGING	COLD BEND				
55A8039-8-*	3.00	4.00	4.00	6.00				
55A8039-6-*	4.00	5.00	4.00	10.0				
55A8039-4-*	5.00	6.00	4.00	10.0				
55A8039-2-*	6.00	8.00	6.00	15.0				
55A8039-1-*	8.00	10.0	6.00	15.0				
55A8039-0-*	8.00	10.0	6.00	15.0				
55A8039-00-*	10.0	12.0	8.00	20.0				
55A8039-000-*	10.0	12.0	8.00	20.0				
55A8039-0000-*	10.0	12.0	8.00	20.0				

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice.

TE Connectivity also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

1/ COLORS AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-681. OTHER CODES AND SUFFIXES MAY BE ADDED TO THE PART NUMBER, AS NECESSARY, TO CAPTURE ANY ADDITIONAL REQUIREMENTS IMPOSED BY THE PURCHASE ORDER.

Nomex, Raychem, TE Connectivity, and TE connectivity (logo) are trademarks.

DIMENSIONS ARE IN INCHES AND, UNLESS OTHERWISE DESIGNATED, ARE NOMINAL.

THIS SPECIFICATION SHEET TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HEREIN. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BID.



Raychem Wire & Cable 501 Oakside Avenue Redwood City, CA 94063-3800 Phone: 1-800-522-6752 Fax: 1-650-361-6297



SPECIFICATION CONTROL DRAWING

Page Revision

2 of 2

J

SCD

55A8039

WIRE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 150°C

Maximum continuous conductor temperature VOLTAGE RATING: 600 volts (rms) at sea level

ACCELERATED AGING (CROSSLINKING PROOF): 300 ± 3°C for 7 hours

BLOCKING: 200 ± 3°C for 24 hours

BRAID COLOR: Dark green preferred, munsell color limits 5Y 3/2 and 5B 2/0.5

CONCENTRICITY: 70% (minimum) FLAMMABILITY: Procedure 1,

3 seconds (maximum), 3 inches (maximum); no flaming of facial tissue

HUMIDITY RESISTANCE: Insulation Resistance,

3000 megohms for 1000 ft. (minimum)

IMMERSION: Diameter increase 5% (maximum); no cracking, no dielectric breakdown

INSULATION ELONGATION AND TENSILE STRENGTH:

Primary Insulation,

Tensile Strength, 5000 lbf/in² (minimum)

Total Insulation (primary insulation and jacket)

Elongation, 75% (minimum)

Tensile Strength, 5000 lbf/in² (minimum)

INSULATION FLAWS:

Primary Insulation,

Spark Test, 1.5 kV (rms) at 60 Hz

4.2 kV (rms) at 3 kHz

Impulse Dielectric Test, 6.0 kV (peak)

Finished Wire,

Spark Test, 5.7 kV (rms) at 3 kHz Impulse Dielectric Test, 8.0 kV (peak)

INSULATION RESISTANCE: 3000 megohms for 1000 ft. (minimum) INSULATION THICKNESS: 0.003 in. (minimum), primary insulation 0.004 in. (minimum), outer jacket

0.009 in. (minimum), total Insulation

JACKET COLOR: White

LIFE CYCLE: 200 ± 3°C for 500 hours

LOW TEMPERATURE-COLD BEND: -65 ± 3°C for 4 hours

SHRINKAGE: 200 ± 3°C for 6 hours, 0.125 in. (maximum) in 12 inches

SMOKE TEST: 200 ± 2°C, no visible smoke

SURFACE RESISTANCE: 500 megohms-in. (minimum), both readings

THERMAL SHOCK RESISTANCE: 150 ± 3°C.

0.100 in. (maximum), AWG 8

0.125 in. (maximum), AWG 6-0000

VOLTAGE WITHSTAND (Post Environmental): 2500 volts (rms), 60 Hz

WICKING: 2.25 in. (maximum) WRAP TEST: 200 ± 3°C for 2 hours

1/ PART NUMBER:

The "*" in the part numbers in Tables I and II shall be replaced by a color code designator.

5D shall be used to designate dark green.

Example: AWG 8, dark green braid: 55A8039-8-5D

AWG 8, white braid: 55A8039-8-9

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

<u>TE Connectivity</u>: 22759/34-2-9