
UltraThin Ceramic Capacitors









The Ultrathin (UT) series of ceramic capacitors is a new product offering from AVX. The UT series was designed to meet the stringent thickness requirements of our customers. AVX developed a new termination process (FCT - Fine Copper Termination) that provides unbeatable flatness and repeatability. The series includes products < 0.35mm in height and is targeted for applications such as Smart cards, Memory modules, High Density SIM cards, Mobile phones, MP3 players, and embedded solutions.

HOW TO ORDER



RECOMMENDED SOLDER PAD DIMENSIONS (Sn Termination) mm (inches) mm (inches)





TYPICAL Cu THICKNESS

	TT
μM	10.0 ± 4.00
mil	0.40 ± 0.16

PART DIMENSIONS

mm (inches)

Thickness	L	W	Т	BL
D	1.00 ± 0.10	0.50 ± 0.10	0.25 ± 0.05	0.27 ± 0.05
	(0.039±0.004)	(0.020 ± 0.004)	(0.010 ± 0.002)	(0.0108 ± 0.002)
E	1.00 ± 0.10	0.50 ± 0.10	0.20 ± 0.05	0.27 ± 0.05
	(0.039±0.004)	(0.020 ± 0.004)	(0.008 ± 0.002)	(0.0108 ± 0.002)
F	1.00 ± 0.10	0.50 ± 0.10	0.125 ± 0.025	0.27 ± 0.05
	(0.039±0.004)	(0.020 ± 0.004)	(0.005 ± 0.001)	(0.0108 ± 0.002)

CAP RANGE (THICKNESS CODE)

X5R	Thickness Code									
YOU			D				E			=
Cap (nF)	6.3V	10V	16V	25V	50V	6.3V	10V	16V	6.3V	10V
1										
10										
22										
33										
47										
68										
100										

X7R	Thickness Code						
A/n		F					
Cap (nF)	6.3V	10V	16V	25V	6.3V		
1							
10							



UltraThin Ceramic Capacitors



UT Series Specifications and Test Methods - Cu Termination

Parameter/Test		Specification Limits	Measuring Conditions		
Operating Temperature Range		-55°C to +85°C	Temperature Cycle Chamber		
Capacitance		Within specified tolerance	Freq.: 1.0 kHz ± 10%		
Dissipation Factor		≤ 3.0% for ≥ 25V DC rating	Voltage: 1.0Vrms ± .2V		
Dissipation	on ractor	\leq 12.5% for \leq 16V DC rating			
Insulation	Pacietanca	100 ΜΩ - μF	Charge device with rated voltage for		
Ilisulation	nesistance	100 Ινίε2 - μι	120 ± 5 secs @ room temp/humidity		
		No breakdown or visual defects	Charge device with 300% of rated voltage for		
Dielectric	Strength		1-5 seconds, with charge and discharge		
			current limited to 50 mA (max)		
	Appearance	No defects	Deflection: 2mm		
	Capacitance	≤ ±12%	Test Time: 30 seconds		
Resistance to	Variation	3 ±12/0	1mm/sec		
Flexure	Dissipation	Meets Initial Values (As Above)	V		
Stresses	Factor				
	Insulation	≥ Initial Value x 0.3			
	Resistance	≥ miliai value x 0.3	◆ 90 mm →		
	Appearance	No visual defects			
	Capacitance	≤ ±20%	Charge device with 1.5X rated voltage in test chamber set at 85°C ± 2°C for 1000 hours (+48, -0)		
Load Life	Variation	\$ 12070			
	Dissipation	<pre>c loitiol \/alua \(\chi \) \(\chi \)</pre>			
	Factor	≤ Initial Value x 2.0 (As Above)			
	Insulation	> laikial \/aliva v O O /A a Alaaysa\	Remove from test chamber and stabilize		
	Resistance	≥ Initial Value x 0.3 (As Above)	at room temperature for 24 ± 2 hours		
	Dielectric	Moote Initial Values (As Above)	before measuring.		
	Strength	Meets Initial Values (As Above)			



UltraThin Ceramic Capacitors



UT Series Specifications and Test Methods – Sn Termination

Parameter/Test		Specification Limits	Measuring Conditions			
Operating Temperature Range		-55°C to +85°C	Temperature Cycle Chamber			
Capac	itance	Within specified tolerance	Freg.: 1.0 kHz ± 10%			
Dissipation Factor		≤ 3.0% for ≥ 25V DC rating	Voltage: 1.0 Vrms ± 0.2 V			
		≤ 12.5% for ≤ 16V DC rating	ŭ .			
Insulation Resistance		100 ΜΩ - μF	Charge device with rated voltage for 120 ± 5 secs @ room temp/humidity			
Dielectric	Strength	No breakdown or visual defects	Charge device with 300% of rated voltage for 1-5 seconds, with charge and discharge current limited to 50 mA (max)			
	Appearance	No defects	Deflection: 2mm			
Resistance to	Capacitance Variation	≤ ±12%	Test Time: 30 seconds 7 1mm/sec			
Flexure Stresses	Dissipation Factor	Meets Initial Values (As Above)				
	Insulation Resistance	≥ Initial Value x 0.3	90 mm			
Solder	rability	≥ 95% of each terminal should be covered with fresh solder	Dip device in eutectic solder at 245 ± 5°C for 5.0 ± 0.5 seconds			
	Appearance	No defects, <25% leaching of either end terminal				
	Capacitance Variation	≤ ±7.5%	Dip device in eutectic solder at 260°C for 60			
Resistance to	Dissipation Factor	Meets Initial Values (As Above)	seconds. Store at room temperature for 24 hours before measuring electrical propertie			
Solder Heat	Insulation Resistance	Meets Initial Values (As Above)	Trodis before measuring electrical properties.			
	Dielectric Strength	Meets Initial Values (As Above)				
	Appearance	No visual defects				
	Capacitance Variation	≤ ±12%	Charge device with 1.5X rated voltage in test chamber set at			
Load Life	Dissipation Factor	≤ Initial Value x 2.0 (As Above)	85°C ± 2°C for 1000 hours (+48, -0)			
	Insulation Resistance	≥ Initial Value x 0.3 (As Above)	Remove from test chamber and stabilize at room temperature for 24 ± 2 hours			
	Dielectric Strength	Meets Initial Values (As Above)	before measuring.			
Load Humidity	Appearance	No visual defects	Store in a test chamber set at 85°C ± 2°C/			
	Capacitance Variation	≤ ±12%	85% ± 5% relative humidity for 1000 hours (+48, -0) with rated voltage applied.			
	Dissipation Factor	≤ Initial Value x 2.0 (As Above)	Remove from chamber and stabilize at			
	Insulation Resistance	≥ Initial Value x 0.3 (As Above)	room temperature and humidity for 24 ± 2 hours before measuring.			
	Dielectric Strength	Meets Initial Values (As Above)	Z4 ± Z Hours before Measuring.			

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

AVX:

```
        UT02YC104MAT2B
        UT023D103MAT2C
        UT026D103MAC2F
        UT02ZD23MAT2D
        UT026D103MAT2D
        UT026D103MAT2D
        UT026D103MAT2E
        UT024D103MAT2E
        UT024D103MAT2E
        UT024D103MAT2E
        UT024D103MAT2E
        UT024D103MAT2E
        UT024D103MAT2E
        UT024D103MAT2E
        UT024D103MAT2E
        UT024D103MAT2D
        UT024D103MAT2D
        UT024D103MAT2D
        UT024D103MAT2D
        UT023C102MAC2E
        UT023C102MAC2E
        UT023C102MAC2E
        UT023D102MAC2E
        UT023D102MAC2E
        UT023D102MAC2D
        UT024D102MAC2D
        UT024D10
```